NONDESTRUCTIVE TESTING USED ON TIMBER IN SPAIN: A LITERATURE REVIEW

Daniel F. Llana^{1,2,}, Guillermo Íñiguez-González^{1,3}, M. Rafael Díez^{1,4}, Francisco Arriaga^{1,3}*

ABSTRACT

Nondestructive testing (NDT) includes several highly efficient techniques for the estimation of the physical and mechanical properties of structural timber. Apart from visual grading, scientific research using Nondestructive testing on timber has been used in Spain since the 1990s. Nondestructive testing can be used for two different purposes: timber grading and the assessment of existing timber structures. The most common devices used in Spain are portable ones based on ultrasound, stress waves, vibration and probing techniques. Many statistical linear models for estimating the mechanical properties of new sawn timber and timber from existing structures have been proposed. Furthermore, several factors that affect Nondestructive testing measurements have been studied (moisture content, temperature, specimen dimensions, sensors position-grain angle, among others) and adjustment factors have also been proposed. Species have been characterized for visual grading standards from the 1980s to date. The large number of research works using different species, devices and procedures shows the need of homogenization and standardization of Nondestructive testing use. This paper presents a review of research works using Nondestructive testing on timber in Spain, in order to add to knowledge, elucidate the concepts to unify Nondestructive testing used and promote research group collaboration in the near future.

Keywords: Acoustic techniques, nondestructive testing, stress waves, structural timber, ultrasound waves, vibration techniques.

INTRODUCTION

Scientific research into the determination of timber mechanical properties began in Spain in the 1960s, in the INIA Structural Timber Laboratory (Figure 1a). Arriaga *et al.* (1992) published the first scientific research work using Nondestructive Testing (NDT) on timber in Spain. The Steinkamp BP-V (BPV), a portable ultrasound device with exponential tip 50 kHz sensors, was used on 34 pieces from existing structures to estimate their mechanical properties with determination coefficients (R^2) between the modulus of elasticity (MOE) and the dynamic modulus of elasticity (E_{dyn}) of 37 % (Figure 1b). Martínez (1992) used the same NDT device on structural maritime pine timber (40 mm x 100 mm and 50 mm x 150 mm) in his PhD thesis. Bucur *et al.* (1993) presented the first SCI JCR publication in Spain of NDT on timber using the BPV and X-ray for fungal decay detection in pine and European beech. Several other works were presented with a focus on detecting decay and defects using ultrasound waves (Palaia *et al.* 1993, Galvañ *et al.* 1994, Martín 1994, Troya and Navarrete 1994). Rodríguez-Liñán and Rubio (1995) and Rubio (1997) estimated MOE and bending strength (MOR)

¹Timber Construction Research Group, Universidad Politécnica de Madrid, Madrid, Spain.

²Timber Engineering Research Group, National University of Ireland Galway, Galway, Ireland.

³Department of Forestry and Environmental Engineering and Management, Montes (School of Forest Engineering and Natural Resources), Universidad Politécnica de Madrid, Madrid, Spain.

⁴Structural Timber Laboratory, Forest Products Department, INIA-CIFOR, Madrid, Spain.

*Corresponding author: daniel@llana@gmail.com

Received: 01.01.2019 Accepted: 01.12.2019

of new Scots pine timber, timber from existing structures and small clear specimens using the BPV with a R^2 from 36 % to 44 % for MOE and MOR, respectively. Pedras *et al.* (1997) estimated MOE from velocity, with a R^2 of 81 % in small clear sweet chestnut specimens. Palaia *et al.* (2000) proposed models for density (ρ) estimation from needle penetration resistance (NPR) depth using the Pilodyn with a R^2 of 80 % using small clear specimens of Scots, maritime and Caribbean pitch pine. Riesco (2001) used BPV velocity to estimate the MOE of small clear specimens of European oak with a 40 % R^2 . At the end of the 1990s an automatic bending classification machine, the Cook Bolinders (SG-AF Tecmach Ltd., St. Albans, UK), arrived in the INIA Structural Timber Laboratory (Figure 1c). Hermoso (2001) reported the settings used to classify Spanish Scots pine with this machine, and Conde (2003) presented the settings for Salzmänn pine. Furthermore, both doctoral theses also estimated structural timber MOE and MOR from ultrasound wave velocity using the Sylvatest (Syl) portable device combined with visual grading parameters.

Acoustic techniques (ultrasound and stress waves)

Esteban (2003) used BPV and Sylvatest Duo (SylDuo) measurements combined with visual parameters to estimate the mechanical properties of Scots and maritime pine from existing structures. Hermoso *et al.* (2003) compared grading results using the Syl and Cook Bolinders, obtaining a lower rejection percentage with the latter for Scots and Salzmänn pine. Arriaga *et al.* (2006) reported a R^2 of 73 % when estimating MOE from SylDuo velocity in missanda. Capuz *et al.* (2007) estimated a C18 strength class based on in-situ SylDuo measurements in the timber structured historic building “Lonja de Mercaderes” in Valencia. Hermoso *et al.* (2007) studied Salzmänn pine round small-diameter timber, estimating MOE from Edyn with a 68 % R^2 . Íñiguez-González (2007) used ultrasound on large cross-section radiata, Scots and Salzmänn pine timber (150 mm x 200 mm, 200 mm x 250 mm) to estimate their properties. Palaia *et al.* (2008) presented a procedure for the assessment of timber structures using several NDT techniques, testing them on Scots pine from existing structures. Basterra *et al.* (2009) evaluated historic buildings in “Chinchón Plaza Mayor” using ultrasound and probing techniques. Carballo *et al.* (2009a), Carballo *et al.* (2009b) presented a review of 30 years of NDT, together with an estimation of maritime pine MOE using the SylDuo and MicroSecond Timer (MST) velocity with a R^2 of 55 % and 70 % with the Edyn. In the case of MOR, a R^2 of 39 % was found when a knottiness parameter was included. Esteban *et al.* (2009) estimated MOE and MOR by stress waves and probing methods using the Íñiguez-González (2007) models, and assigned a strength class in the assessment of the Valsain sawmill historic building (Figure 1d). Atienza-Conejo (2012) used pulse-echo ultrasound to detect xylophage insect attack in timber ships. Casado *et al.* (2012) estimated the MOE of black poplar timber by combining SylDuo velocity and visual parameters with a R^2 of 68 %. Montón (2012) tested Catalanian radiata pine, estimating its properties with ultrasound and stress waves. Vega *et al.* (2012) estimated the mechanical properties of sweet chestnut using the Sylvatest Trio (SylTrio) and MST, obtaining a R^2 of 70 % using Edyn or velocity and density. However, MOR was estimated with a R^2 of 27 % even when a knottiness parameter was included. Merlo *et al.* (2014) used the IML Micro Hammer (IML MH) device (IML, Wiesloch, Germany) on standing maritime pine trees estimating the MOE of sawn boards from these trees with a R^2 of 55 %. Vázquez *et al.* (2015) used 13 polyhedral small clear specimens of sweet chestnut to determine Young’s moduli, shear moduli and Poisson’s ratios by ultrasound with 1 MHz sensors, finding a good correlation with MOE of structural timber. Vilches *et al.* (2015) assigned strength classes C14 and C18 to Scots pine beams from an existing structure by stress waves using the Íñiguez-González (2007) models. Abián and Segura (2016) estimated the residual capacity of fire-damaged Scots pine timber from existing structures using the ultrasound wave method. Llana (2016) used the USLab device with 45 kHz sensors to estimate MOE from Edyn with a R^2 of 90 %. Crespo *et al.* (2017) tested small clear specimens of southern blue gum with 1 MHz ultrasound sensors to obtain their elastic values. Morales-Conde and Machado (2017) used PUNDITplus (Proceq, Schwerzenbach, Switzerland) with 54 kHz sensors and MST on 30 clear wood pieces of maritime pine to estimate MOE from Edyn. Higher R^2 (91 %) combining MST measurements at different depths than using PUNDIT (71 %) was found. Hillig *et al.* (2018) used SylDuo, USLab and MST devices to study wood-polymer-composites in the Universidad Politécnica de Madrid Timber Laboratory. Osuna-Sequera *et al.* (2019a) studied several criteria to determine the cross-section in existing timber structures to estimate MOE from Edyn. Vega *et al.* (2019a) estimated MOE of 216 dry sweet chestnut small-diameter logs using MST velocity and Edyn with R^2 of 64 % and 67 %, respectively and a grading system was designed based on MST velocity.

Figure 1: Spanish scientific timber research facts: a) INIA Structural Timber Laboratory in the 1960s and 1970s. b) Arriaga *et al.* (1992) ultrasound measurements. c) Cook Bolinders, INIA Structural Timber Laboratory. d) Valsaín sawmill historic building.

Vibration techniques

Arriaga *et al.* (2005a) published the first scientific research work done in Spain with vibration technique to grade 75 radiata pine specimens using the Portable Lumber Grader (PLG). Broto *et al.* (2007) tested 211 specimens of Scots pine using the Mechanical Timber Grader (MTG), finding that 73 % of the specimens were undergraded and 7 % were overgraded. Íñiguez-González (2007) applied the PLG to large cross-timber of radiata, Scots and Salzmänn pine, obtaining similar R^2 for MOE estimation from vibration and ultrasound velocity. Santaclara *et al.* (2009) tested 200 sawn timber pieces of Douglas fir containing a large amount of juvenile wood using PLG, and they found a better R^2 in MOE estimation which combined velocity and knottiness parameters rather than velocity and density. Villanueva (2009) tested Spanish juniper round wood by longitudinal vibration, obtaining a R^2 of 43 % when estimating MOE by combining Edyn and conicity parameters. Rojas *et al.* (2011) used a microphone to record the natural frequencies of veneer samples for species identification. Santaclara and Merlo (2011) used the Hitman Director HM200 (HM200) on 162 logs of maritime pine before testing sawn timber from them. A R^2 of 73 % was reported when estimating sawn timber MOE from logs using the Edyn. Arriaga *et al.* (2012) published the preliminary grading settings for European standard EN 14081-2 (2010) of PLG for Spanish radiata, Scots and Salzmänn pine, but were not implemented in the Spanish industry. Montero (2013) tested Scots pine sawn timber with several NDT devices, concluding that PLG results are the best mechanical property estimators. Vega (2013) compared sweet chestnut results from two different vibration devices, the PLG with a microphone and the HM200 with a contact accelerometer, finding better mechanical properties estimation with the PLG measurements. Arriaga *et al.* (2014) estimated radiata pine mechanical properties based on longitudinal and transversal vibration with similar accuracy. Llana (2016) used the PLG with a microphone and the MTG with a contact accelerometer to estimate MOE with a 91 % R^2 and MOR at 70 % using the Edyn, and found no significant differences between the results of both devices. Osuna-Sequera (2017) tested 11 m long large cross-section Salzmänn pine beams from an 18th century timber structure using the PLG and estimating MOE using the Edyn with an 80 % R^2 . Not only restraint-free isolated specimens were analyzed using the vibration technique, as multiple contact accelerometers were also used to evaluate timber structures. Baño *et al.* (2011) studied resonance risk in Scots pine timber footbridges, while Castro-Triguero *et al.* (2017) evaluated a 125 m length timber footbridge and Arce-Blanco (2017) tested Salzmänn pine plank timber arches. Currently, the first research experience on vibration testing of light frame timber floors in Spain is carried out by the Timber Structures and Wood Technology Research Group of the University of Valladolid, after developing their own accelerometers (Villacorta-Calvo *et al.* 2019). Furthermore, scientists from the previous research group patented a transversal vibration system using several microphone receptors for the evaluation of existing timber structures (Gutiérrez-Sánchez *et al.* 2019).

Probing techniques

Probing methods (needle and drill penetration resistance, screw and nail withdrawal resistance) are mainly used to estimate density in existing timber structures. Palaia *et al.* (2000) used the Pilodyn to estimate the density of small clear specimens of Scots, maritime and Caribbean pitch pine. Casado *et al.* (2005) predicted density using the Screw Withdrawal Resistance Meter (SWRM) on 39 Scots pine joists from an existing structure. Bobadilla *et al.* (2007) estimated density using the Pilodyn and SWRM on 395 large cross-section specimens of radiata, Scots and Salzmänn pine with a R^2 of 35 % and 49 %, respectively. Íñiguez-González *et al.* (2010) proposed estimation density models for large cross-section radiata, Scots, Salzmänn and maritime pine, finding a better R^2 with probing techniques than was the case with ultrasound waves. Montón (2012) introduced core drilling technique for density estimation in Spain, obtaining a higher R^2 than was the case with the Pilodyn or SWRM in radiata pine. Bobadilla *et al.* (2013) presented the definitive prototype of the RML Wood Extractor (GICM-UPM, Madrid, Spain) in a NDT wood conference in Madison, WI, USA. The device was designed to be coupled to a commercial drill to collect all of the chips produced during drilling inside a paper bag filter. Density is determined from the mass of chips and the volume of the hole. The UNE 41809 (2014) was published for use of the penetrometer in wood elements to diagnose existing buildings. Íñiguez-González *et al.* (2015a) compared density estimation by using the Pilodyn, SWRM and core drilling, obtaining the highest R^2 with the latter. Bobadilla *et al.* (2018) estimated density by core drilling technique on small clear specimens of 10 species with a R^2 of 98 %. Llana *et al.* (2018a) presented a comparison between the Pilodyn, Wood Pecker, SWRM, core drill and RML WoodEx for density estimation of Norway spruce from an existing timber structure, obtaining a better R^2 with the core drill and RML WoodEx. The drilling resistance technique using Resistograph and IML Resi devices was used to evaluate timber structures (Capuz *et al.* 2007, Basterra *et al.* 2009, Touza 2009, Montoya-Morguá 2010, González-Sanz 2012, Lozano *et al.* 2013, Abián and Segura 2016) and also for density estimation (Mariño *et al.* 2002, Casado *et al.* 2005, Vilches and Correal 2009, So-to-Martínez 2010, Acuña *et al.* 2011, Morales-Conde *et al.* 2014, Camacho-Valero 2017).

Other NDT techniques

Neuronal networks using data from NDT were studied for timber grading (Mier 2001, García-Esteban *et al.* 2009, García-de-Ceca *et al.* 2013, García-Iruela *et al.* 2016, Villasante *et al.* 2019). Mariño *et al.* (2010) studied the influence of pith distance on velocity using acoustic tomography. Rodríguez-Abad *et al.* (2011) used ground-penetrating radar (GPR) on 22 maritime pine joists to estimate MC and Martínez-Sala *et al.* (2013) studied the differences between longitudinal and transversal GPR measurements. Morales-Conde *et al.* (2013) used infrared thermography (IRT) to detect MC differences. Oliver and Abián (2013) developed a sensor to monitor timber structures for termites using light emission and fungi risk by moisture content estimation. Sánchez-Beitia *et al.* (2015) presented the application of Hole-Drilling technique on small clear specimens of radiata pine for stress quantification, and Crespo-de-Antonio *et al.* (2016) used it to assess two existing timber structures. López *et al.* (2018) estimated wood density from the variation of surface temperature when specimens are cooled using IRT. Ruano *et al.* (2019) determined the ratio of juvenile wood to mature wood using near infrared-hyperspectral imaging.

Adjustment factors

The results of NDT are affected by several factors: moisture content (MC), temperature (T), specimen dimensions, sensor positioning and grain angle and timber-sensor coupling, to mention just a few. Íñiguez-González *et al.* (2015b) published a compilation of NDT adjustment factors from the national and international literature. Rodríguez-Liñán and Rubio (1995), Rodríguez-Liñán and Rubio (2000) and Palaia *et al.* (2000) published some of the first Spanish studies of MC influence on NDT measurements using the BPV. Regarding T, Llana *et al.* (2014) reported the influence of T on NDT, showing a clear linear tendency below 0°C and no significant tendency above 0°C for dry Scots pine small clear specimens. The length effect was found several times in ultrasound velocity using the SylDuo (Arriaga *et al.* 2006, Acuña *et al.* 2007, Íñiguez-González *et al.* 2007a, Llana *et al.* 2013) and an adjustment procedure was proposed (Llana *et al.* 2016). The influence of dimension was also reported on the velocity obtained by vibration using PLG (Carballo *et al.* 2007, Casado *et al.* 2010). Concerning sensor position with respect to the grain, Rodríguez-Liñán and Rubio (1995) observed a ratio between face to face and end to end velocity (V_f/V_0) of 1,19 and between perpendicular and longitudinal velocity (V_{90}/V_0) of 2,9. Esteban (2003) found a V_{90}/V_0 of 4 and Íñiguez-González *et al.* (2009) found this to stand at from 2,5 to 3. Several authors proposed adjustments depending on the angle respect to the grain (Acuña *et al.* 2007, Arriaga *et al.* 2009, Balmori *et al.* 2016). Arriaga *et al.* (2017a) found differences between the velocity obtained in end-to-end measurements and surface or crossed measurements equal to or less than 4,4 % on average.

Visual grading

Visual grading is the oldest nondestructive timber evaluation technique. The first Spanish visual grading standard UNE 56525 (1972) was published in December 1972 for structural timber. Seven visual grades were defined (Extra/100, I/80, II/70, III/60, IV/50, V/40 y VI). Argüelles and Arriaga (1986) published a visual grading proposal based on a British standard, with four visual grades for sawn timber (75, 65, 50 and 40) and three for glulam lamellas (LA, LB and LC). A new visual grading standard UNE 56544 (1997) was first published in 1997, first covering softwood and hardwood species (*radiata*, Scots and maritime pine, black poplar and southern blue gum). Two years later Salzmänn pine was also included and afterwards black poplar was excluded. In 2007 a specific standard only for hardwoods was published as UNE 56546 (2007), and the current version of this standard from 2013 is applied to southern blue gum and sweet chestnut, while UNE 56544 (2011) is now only for softwoods. Furthermore, UNE 56547 (2018) is a visual grading standard for Scots and Salzmänn pinewood overhead poles. Nowadays national visual grading standards should follow the minimum requirements established by European standard EN 14081-1 (2016). Furthermore, in order to homogenize the national visual grades in all European countries, EN 1912 (2012) related national visual grades with the strength classes according to EN 338 (2016). Concentrated Knot Diameter Ratio (CKDR) is a visual parameter used frequently in combination with NDT ultrasound and vibration results. CKDR includes the influence of knots as the main defect in prediction models, improving the estimation of MOR. This parameter has often been used in Spanish research works, mainly for the assessment of existing structures.

Furthermore, the first research experience of NDT evaluation (using most of the techniques previously cited) of recovered wood from deconstruction and demolition for reuse and recycling purposes is being gained by the Timber Construction Research Group of the Universidad Politécnica de Madrid (Íñiguez-González et al. 2019).

The main goal of this paper is to present the history of wood NDT used in Spain and its main milestones with three objectives. (1) To allow different Spanish and international research groups to have a better knowledge of these works. (2) To elucidate concepts to unify NDT used on timber and future standardization procedures. (3) To promote research group cooperation and exchange activities.

Summary of species and devices used in the literature

Species

Structural sawn timber, round wood and small clear specimens from several Spanish-grown species tested with NDT methods were found in the literature: *radiata* pine (*Pinus radiata* D. Don), Scots pine (*Pinus sylvestris* L.), Salzmänn pine (*Pinus nigra* Arnold ssp. *salzmannii* (Dunal) Franco), Corsican pine (*Pinus nigra* Arnold ssp. *laricio* (Poir.) Maire), maritime pine (*Pinus pinaster* Ait. ssp. *mesogeensis* Fieschi & Gaussen and *Pinus pinaster* Ait. ssp. *atlantica* H. de Vill.), Aleppo pine (*Pinus halepensis* Mill.), black poplar (*Populus x euramericana* (Dode) Guinier), southern blue gum (*Eucalyptus globulus* Labill.), sweet chestnut (*Castanea sativa* Mill.), Douglas fir (*Pseudotsuga menziesii* (Mirb.) Franco), silver fir (*Abies alba* Mill.), robinia (*Robinia pseudoacacia* L.), Japanese larch (*Larix kaempferi* (Lamb.) Carr.), Spanish juniper (*Juniperus thurifera* L.), European beech (*Fagus sylvatica* L.), European oak (*Quercus robur* L.) and Paulownia (*Paulownia elongata* S.Y.Hu). Some other abroad-grown species but sawn and commercialized in Spain for structural purposes were also found in the literature: missanda (*Erythrophleum ivorense* A. Chev. and *Erythrophleum suaveolens* (Guill. & Perr.) Brenan), iroko (*Milicia excelsa* (Welw.) C. C. Berg and *Milicia regia* (A. Chev.) C. C. Berg), Norway spruce (*Picea abies* (L.) Karst.), southern pine (*Pinus tadea* L.), American pitch pine (*Pinus pallustris* Mill.), Caribbean pitch pine (*Pinus caribaea* Morelet) and western red cedar (*Thuja plicata* Donn.).

The NDT devices used in Spain are usually portable, and the most common ones cited in the literature are:

Ultrasound and stress wave devices

Ultrasound and stress wave time-of-flight (ToF) is recorded. The most common devices are: (1) The Steinkamp BP-V (Ultratest, Achim, Germany) ultrasound device (600 V output power) equipped with 50 kHz exponential tip sensors (Figure 2a), (2) The Sylvest Duo (220-250 V output power) and the Trio (CBS-CBT, Lausanne, Switzerland) instrument equipped with conical 22 kHz sensors (Figure 2b, Figure 2c), (3) The USLab (Agricef, Campinas, Brazil) ultrasound device (700 V output power and 0,1 µs resolution) which can be used with different sensors from 20 to 90 kHz (Figure 2e), (4) The MicroSecond Timer (Fakopp, Sopron, Hungary) an impact stress wave device (Figure 2d). Velocity is calculated by dividing length over ToF.

Figure 2: NDT devices: a) Steinkamp BP-V. b) Sylvatest Duo. c) Sylvatest Trio. d) MicroSecond Timer. e) USLab. f) PLG. g) Hitman HM 200 (courtesy of Dr. Abel Vega). h) MTG.

Vibration devices

Natural frequency data is recorded after inducing vibration by hammer impact. The most common devices found in the literature are: (1) The Portable Lumber Grader PLG (Fakopp, Sopron, Hungary) equipped with a microphone that is placed in front of one end (Figure 2f), (2) The Hitman Director HM 200 (Fibre-gen, Christchurch, New Zealand) equipped with a contact accelerometer (Figure 2g), (3) The Mechanical Timber Grader MTG 960 (Brookhuis, Enschede, Netherlands) equipped with a contact accelerometer (Figure 2h). Velocity from the first mode of natural frequency is calculated as the product of two times length and frequency.

Probing devices

The most common probing devices used in Spain for density estimation and structural inspections found in the literature review are: (1) The Pilodyn 6 J Forest (Proceq, Schwerzenbach, Switzerland) (Figure 3a). This consists of a calibrated spring that releases a 2,5 mm diameter steel needle with a constant energy of 6 J. NPR depth of this needle into the timber is measured in mm. (2) The Wood Pecker (DRC, Ancona, Italy) (Figure 3b). This modified sclerometer inserts a 2,5 mm diameter steel needle by striking several times with constant energy. NPR depth is measured in mm after each strike. (3) The Screw Withdrawal Resistance Meter SWRM (Fakopp, Sopron, Hungary) (Figure 3c). SWR force is measured in kN when a standard screw is pulled out. (4) Commercial core bits with different external diameters, usually from 10 to 22 mm (Figure 3d). The mass and volume of the cylindrical extracted core are measured. (5) The RML Wood Extractor (RML WoodEx) (GICM-UPM, Madrid, Spain) coupled to a commercial drill (Figure 3e). This Spanish design was patented in 2013 (Martínez and Bobadilla 2013) using drilling chips extraction technique. A bit is drilled to a standard depth in wood specimens (so the hollow volume is known) vacuum collecting all of the chips produced during drilling in a paper filter bag. Density is estimated from the mass of chips and volume of the hollow. (6) The Resistograph (RinnTech, Heidelberg, Germany) is a drilling resistance tool where relative resistance is measured against the introduction of a small diameter drill at a constant speed (Figure 3f). (7) The IML Resi (IML, Wiesloch, Germany) uses drilling resistance technique in a similar way to the Resistograph. There are several models, and Figure 3g shows the F400-S. Probing measurements should be taken while avoiding areas close to the pith and other singularities such as knots and resin pockets, etc.

Figure 3: Probing devices: a) Pilodyn 6J Forest. b) Wood Pecker. c) SWRM. d) Core bit. e) RML WoodEx. f) Resistograph (courtesy of Dr. Joaquín Montón). g) IML Resi F400-S.

RESULTS AND DISCUSSION

Acoustic techniques (ultrasound and stress waves) for property estimation

Velocity is calculated from ToF by dividing length over ToF. The dynamic modulus of elasticity (Edyn) is calculated as the product of density and square velocity. Several authors have presented mechanical properties estimation models using velocity and Edyn (Table 1).

Table 1: Mechanical properties estimation models by acoustic techniques.

Device	MOE and MOR models (MPa)	R ² (%)	Species/product	Reference
BPV	MOR ₃₀₀ =1828+0.7777*Edyn	53	Maritime p.	(7)
	MOR ₁₀₀ =20802+6.3434*V ^{0.5}	98	Scots p.	(4)
	MOR ₁₀₀ =41.58+0.0291*V ^{0.37}	70	Sweet chestnut	(8)
BPV	MOR ₁₀₀ =2332+1.2593*V ^{0.37}	81	Scots p.	(10)
	MOR ₁₀₀ =2075+0.1569*Edyn ^{0.37}	60	Scots p.	(10)
	MOR ₁₀₀ =7.31+0.0169*V ^{0.37}	66	Scots p.	(10)
Syl	MOR ₁₀₀ =5.50+0.0035*Edyn	38	Scots p.	(10)
	MOR ₁₀₀ =4.11+0.0025*V ^{0.37}	52	Salzmann p.	(10)
	MOR ₁₀₀ =-114.47+0.0334*V ^{0.37}	40	Salzmann p.	(10)
Syl	MOE ₁₀₀ =-139+0.0065*V ^{0.37}	51	Salzmann p.	(10)
	MOR ₁₀₀ =3660+0.4201*Edyn	40	Scots, maritime p.	(10)
	MOR ₁₀₀ =4.15+0.0023*Edyn	22	Scots, maritime p.	(10)
BPV	MOE ₁₀₀ =423.0676+0.0225*V ^{0.37}	53	Scots p.	(10)
	MOR ₁₀₀ =10862+6.4216*V ^{0.37}	71	Misounda	(10)
SylDuo	MOR ₁₀₀ =-13355+3.5020*V ^{0.37} -1243*dh-13.95*P	65	Scots, Salzmann p.	(15)
	MOR ₁₀₀ =-50.83+0.0330*V ^{0.37} -0.0042*Z ₁ -18.48+0.0043*V ^{0.37} -0.08*P	65	Scots, Salzmann p.	(15)
	MOR ₁₀₀ =-1034+0.8713*V ^{0.37} -10	68	Salzmann p.	(10)
SylDuo	MOE ₁₀₀ =330+0.7548*Edyn+16.55*Zrad+249.10*Zsco+0*Zsal	74	Radiata, Scots,	(16)
	MOR ₁₀₀ =-3.65+0.0014*Edyn+0.5372*Z ₁ +1.19*Zsco+0*Zsal	60	Salzmann p.	(10)
	MOR ₁₀₀ =789+0.7182*Edyn	67	Maritime p.	(10)
MST	MOR ₁₀₀ =2.64+0.0033*Edyn	29	Maritime p.	(10)
	MOR ₁₀₀ =378+0.3609*Edyn	69	Maritime p.	(10)
	MOR ₁₀₀ =0.40+0.0036*Edyn	30	Black poplar	(10)
SylDuo	MOE ₁₀₀ =-14986+2.9825*V ^{0.37} -17.35*P+6.34*dc+36.89*dh-267.79*Pw	68	Black poplar	(10)
	MOR ₁₀₀ =1191+0.0197*Edyn	82	Radiata p.	(10)
	MOR ₁₀₀ =8.38+0.0028*Edyn	40	Radiata p.	(10)
MST	MOR ₁₀₀ =1358+0.0170*Edyn	78	Radiata p.	(10)
	MOR ₁₀₀ =8.33+0.0031*Edyn	40	Radiata p.	(10)
MST	Ln(MOR ₁₀₀)=-16.4037+3.1708*ln(V)+0.03359*Zp	94	Particle board and	(10)
	Ln(MOR ₁₀₀)=-0.2283+0.0026*V+0.0133*Zp	97	MDF	(10)
	MOE ₁₀₀ =-2879+2.3069*V ^{0.37}	36	Black poplar	(10)
MST	MOE ₁₀₀ =12296+2.6860*V ^{0.37} -18.2*P	56	Black poplar	(10)
	MOR ₁₀₀ =384+0.7235*Edyn	56	Black poplar	(10)
SylDuo	MOR ₁₀₀ =-7.63+0.0038*Edyn	31	Scots p.	(10)
	MOR ₁₀₀ =1375+0.0337*Edyn	54	Scots p.	(10)
	MOR ₁₀₀ =1.96+0.0011*Edyn	22	Scots p.	(10)
MST	MOE ₁₀₀ =-1847580+2.44*V ^{0.37}	90	Superpan boards	(10)
	MOR ₁₀₀ =-64.42+7847*V ^{0.37}	90	Superpan boards	(10)
	MOR ₁₀₀ =-108380+3.04*V ^{0.37}	92	Superpan boards	(10)
MST	MOR ₁₀₀ =65.16+72148*V ^{0.37}	93	Superpan boards	(10)
	MOR ₁₀₀ =1529+0.7029*Edyn	71	Sweet chestnut	(10)
	MOR ₁₀₀ =4.90+0.0027*Edyn	14	Sweet chestnut	(10)
SylDuo	MOR ₁₀₀ =3988+0.5670*Edyn	56	Sweet chestnut	(10)
	MOR ₁₀₀ =2.07+0.0019*Edyn	51	Sweet chestnut	(10)
IML MH	MOR ₁₀₀ =-4.54*V ^{0.37} +379.47*BAL+0.06*G ₀ +374.67*H ₀ +125.97*DBH	53	Maritime p.	(10)
	MOE ₁₀₀ =135+0.4479*Edyn	44	Maritime p.	(10)
	MOE ₁₀₀ =135+0.4479*Edyn	44	Maritime p.	(10)
MST	MOE ₁₀₀ =-1471+0.8200*Edyn+438.89*Zrad+893.17*Zsco+329.53*Zsal+0*Zmar	90	Maritime p.	(10)
	MOR ₁₀₀ =-37.72+0.0080*Edyn+12.47*Zrad+3.75*Zsco+11.42*Zsal+0*Zmar	68	Radiata, Salzmann,	(10)
	MOR ₁₀₀ =-335+0.0094*Edyn+51.26*Zrad+183.7*Zsco+339.88*Zsal+0*Zmar	90	Scots, maritime p.	(10)
USLab ⁽¹⁾	MOR ₁₀₀ =-37.51+0.0063*Edyn+12.47*Zrad+4.00*Zsco+11.23*Zsal+0*Zmar	67	Scots, maritime p.	(10)
	MOR ₁₀₀ =-1662+0.78*Edyn+428.70*Zrad+958.05*Zsco+232.23*Zsal+0*Zmar	90	Scots, maritime p.	(10)
	MOR ₁₀₀ =-58.09+0.0077*Edyn+1.92*Zrad+2.17*Zsco+12.17*Zsal+0*Zmar	67	Scots, maritime p.	(10)
BPV	MOR ₁₀₀ =-2521+0.939*Edyn	79	Scots p.	(10)
	MOR ₁₀₀ =-37.06+0.0077*Edyn	53	Scots p.	(10)
	MOR ₁₀₀ =-743+0.0149*Edyn	85	Radiata, Salzmann,	(10)
USLab ⁽¹⁾	MOR ₁₀₀ =-419+0.7483*Edyn	85	Scots, maritime p.	(10)
	MOR ₁₀₀ =-1384+0.9131*Edyn	81	Scots, maritime p.	(10)
PUNDET	MOR ₁₀₀ =-1053+0.9417*Edyn ^{0.37}	71	Maritime p.	(10)
	MOR ₁₀₀ =-1218+1.2330*Edyn ^{0.37}	91	Maritime p.	(10)
	MOR ₁₀₀ =-429+0.8391*Edyn	69	Maritime p.	(10)
USLab ⁽¹⁾	MOR ₁₀₀ =-1023+0.1380*Edyn	70	Salzmann p.	(10)
	MOR ₁₀₀ =-95+0.7727*Edyn	67	Salzmann p.	(10)
	MOR ₁₀₀ =-698+0.8282*Edyn ^{0.37}	42	Salzmann, Scots p.	(10)
MST	MOR ₁₀₀ =-5.02+0.0033*Edyn ^{0.37}	43	Salzmann, Scots p.	(10)
	MOR ₁₀₀ =-4807+0.3577*Edyn	53	Salzmann, Scots p.	(10)
	MOR ₁₀₀ =-3279+0.4421*Edyn	62	Norway spruce ⁽¹⁾	(10)
USLab ⁽¹⁾	MOR ₁₀₀ =-2810+0.5916*Edyn	63	Norway spruce ⁽¹⁾	(10)
	MOR ₁₀₀ =-2810+0.5916*Edyn	63	Norway spruce ⁽¹⁾	(10)
	MOR ₁₀₀ =-2810+0.5916*Edyn	63	Norway spruce ⁽¹⁾	(10)

Measurements in longitudinal direction: V (m·s⁻¹) velocity. Edyn=ρ·V² (MPa).
ρ (kg·m⁻³) density. MOR (MPa). MOE_{loc} (MPa). MOE_{EN384}=MOE*1,3-2690 (MPa).
Zrad, Zsco, Zsal and Zmar are constants for radiata, Scots, Salzmann and maritime pine, which are only equal to 1 for this species, for other species are 0; Zp is a constant for boards, which is equal to 1 for particleboards and 0 for MDF; L (mm) length; dc and dh=knottiness parameters; Rw=ring parameter; BAL, G, H₀ and DBH=forest inventory parameters.
(¹)Small clear specimens,(²)Three-point bending test,(³)Timber from existing structures,(⁴)Round timber,(⁵)45 kHz sensors,(⁶)22 kHz sensors,
(⁷)Martínez 1992,(⁸)Rodríguez-Liñán and Rubio 1995,(⁹)Pedras *et al.* 1997,(¹⁰)Rubio 1997,(¹¹)Hermoso 2001,(¹²)Hermoso *et al.* 2002,(¹³)Conde 2003,(¹⁴)Esteban 2003,(¹⁵)Hermoso *et al.* 2003,(¹⁶)Arriaga *et al.* 2006,(¹⁷)Conde *et al.* 2007,(¹⁸)Hermoso *et al.* 2007,(¹⁹)Íñiguez-González 2007,(²⁰)Carballo *et al.* 2009b,(²¹)Casado *et al.* 2012,(²²)Montón 2012,(²³)Pérez-García 2012,(²⁴)Casado *et al.* 2013,(²⁵)Montero 2013,(²⁶)Sevilla *et al.* 2013,(²⁷)Vega 2013,(²⁸)Merlo *et al.* 2014,(²⁹)Cáceres-Hidalgo 2016,(³⁰)Llana 2016,(³¹)Arriaga *et al.* 2017a,(³²)Morales-Conde & Machado 2017,(³³)Osuna-Sequera 2017,(³⁴)Aira *et al.* 2019,(³⁵)Arriaga *et al.* 2019.

Vibration techniques used to estimate properties

Longitudinal velocity from first mode natural frequency is calculated as the product of two times length and frequency. The dynamic modulus of elasticity (Edyn) was calculated as product of density and square velocity. Several authors have presented estimation models using vibration techniques (Table 2).

Several authors improved the prediction models of MOR by combining acoustic or vibration results with visual parameters. Hermoso (2001) found an absolute R² increase of 11 %, while the corresponding figure for Íñiguez-González (2007) was 15 % and for Arriaga *et al.* (2014) it stood at 4 %, including knottiness parameters.

Table 2: Mechanical properties estimation models by vibration techniques.

Device	MOE and MOR models (MPa)	R ² (%)	Species	Reference
PLG	MOE=-338+1,1136*0,92*Edyn	77	Radiata p.	(3)
	MOR=0,81+0,0039*(0,92*Edyn-6,2*CKDR)	48		
MTG	MOE=-44,50*Edyn ^{0,6305}	50	Scots p.	(4)
	MOR=0,0829*Edyn ^{0,6719}	46		
PLG	MOE _{EN384} =1153+1,04*(0,92*Edyn-6,2*CKDR)	65	Scots p.	(5)
	MOR=-40,53+0,08*f+0,07*p	44		
PLG	MOE=-762+0,9599*Edyn-508,92*Zrad-354,98Zsco+0*Zsal	76	Radiata, Scots, Salzmann p.	(6)
	MOR=-3,85+0,0045*Edyn-10,67*Zrad-3,83*Zsco+0*Zsal	65		
PLG	MOE _{EN384} =-868+1,0022*(0,92*Edyn-6,2*CKDR)	82	Maritime p.	(7)
	MOR=-70,66+0,0746*f+0,0641*p	47		
PLG	MOE _{EN384} =92+0,7927*(0,92*Edyn)	54	Black poplar	(8)
	MOR=-13,08+0,0066*(0,92*Edyn)	41		
PLG	MOE=-13294+12,728*p+3,689*V	82	Douglas fir	(9)
	MOR=-43+0,0172*V	38		
PLG	MOE=-490+6,7702*f+11,10*p-262,72*C ⁽¹⁾	43	Spanish juniper	(10)
PLG	MOE=1642+0,8251*Edyn-1041,87*Zrad-176,01*Zsco+0*Zsal	72	Radiata, Scots, Salzmann p.	(11)
	MOR=1,30+0,0038*Edyn-13,25*Zrad-3,01*Zsco+0*Zsal	61		
PLG	MOE _{EN384} =-13704+2,9563*V+17,85*p+307,72*dc+62,86*dh-267,59*Rw	70	Black poplar	(12)
PLG	MOE=1538+0,7490*Edyn	85	Radiata p.	(13)
	MOR=7,95+0,0035*Edyn	47		
PLG	MOE=(-15+0,0040*V+0,0160*p-0,0010*L)*1000	74	Sweet chestnut	(14)
	MOR=-50,08+0,0034*Edyn-22,0590*kh ^{1/2} -0,0090*L	33		
PLG	MOE=353+0,8734*Edyn	63	Scots p.	(15)
	MOR=-9,37+0,0048*Edyn	37		
PLG ⁽⁷⁾	MOE=3627+0,5564*Edyn	45	Sweet chestnut	(16)
	MOR=10,37+0,0028*Edyn	26		
PLG	MOE=1481+0,8230*Edyn	78	Sweet chestnut	(16)
	MOR=3,59+0,0036*Edyn	20		
HM200	MOE=2494+0,7270*Edyn	70	Radiata p.	(17)
	MOR=12,46+0,0028*Edyn	15		
PLG	MOE=1229+0,7566*Edyn	87	Radiata p.	(17)
	MOR=7,26+0,0035*Edyn	46		
PLG ⁽⁷⁾	MOE=823+0,8112*Edyn	86	Paulownia	(18)
	MOR=3,25+0,0040*Edyn	50		
PLG	MOE _{EN384} =357+0,5222*(0,92*Edyn)	42	Radiata, Salzmann, Scots, maritime p.	(19)
PLG ⁽¹⁴⁾	MOE _{EN384} =-2436+0,9053*Edyn	41		
PLG	MOE=-226+0,90*Edyn-144,26*Zrad+1105,25*Zsco+814,85*Zsal+0*Zmar	92	Radiata, Salzmann, Scots, maritime p.	(20)
	MOR=-25,99+0,0087*Edyn-9,72*Zrad-1,80*Zsco-6,72*Zsal+0*Zmar	70		
MTG	MOE=-327+0,90*Edyn-139,37*Zrad+1119,60*Zsco+782,94*Zsal+0*Zmar	92	Salzmann p. (21)	(20)
	MOR=-26,92+0,0088*Edyn-9,66*Zrad-1,65*Zsco-7,03*Zsal+0*Zmar	70		
PLG	MOE=-740+0,9507*Edyn	80	Radiata p.	(21)
HM200	MOE _{EN384} =5353+3,4*V	50	Maritime p.	(21)
	MOE _{EN384} =2160+2*V	43		

Measurements in longitudinal or transversal ⁽⁷⁾ direction: V (m·s⁻¹) velocity. Edyn=ρ·V² (MPa). ρ (kg·m⁻³) density. f (Hz) frequency. MOR (MPa). MOE (MPa). MOE_{loc} (MPa). MOE_{EN384}=MOE*1,3-2690 (MPa). Zrad, Zsco, Zsal and Zmar are constants for radiata, Scots, Salzmann and maritime pine, which are only equal to 1 for this species, for other species are 0; L (mm) length; CKDR, kh, dc and dh=knottiness parameters; C=taper parameter; Rw=ring parameter. ⁽⁷⁾Transversal measurements, ^(7C)Transversal measurements on cantilever beam, ⁽¹⁾Round timber, ⁽²⁾Timber from existing structures, ⁽³⁾Arriaga *et al.* 2005^a, ⁽⁴⁾Broto *et al.* 2007, ⁽⁵⁾Casado *et al.* 2007, ⁽⁶⁾Íñiguez-González 2007, ⁽⁷⁾Casado *et al.* 2008, ⁽⁸⁾Casado *et al.* 2009, ⁽⁹⁾Santaclara *et al.* 2009, ⁽¹⁰⁾Villanueva 2009, ⁽¹¹⁾Arriaga *et al.* 2012, ⁽¹²⁾Casado *et al.* 2012, ⁽¹³⁾Montón 2012, ⁽¹⁴⁾Vega *et al.* 2012, ⁽¹⁵⁾Montero 2013, ⁽¹⁶⁾Vega 2013, ⁽¹⁷⁾Arriaga *et al.* 2014, ⁽¹⁸⁾Cáceres-Hidalgo 2016, ⁽¹⁹⁾Llana 2016, ⁽²⁰⁾Osuna-Sequera 2017, ⁽²¹⁾Vega *et al.* 2019b.

Probing techniques for density estimation

According to several authors (Bobadilla *et al.* 2007, Íñiguez-González 2007, Calderón 2012, Martínez 2016) no significant differences were found between radial and tangential measurements (with respect to annual rings). Furthermore, in the assessment of timber structures (the most common use for probing techniques) it is not usually possible to select the probing direction. Density estimation models using acoustic and probing techniques have been presented by several Spanish authors (Table 3).

Table 3: Density estimation models from Spanish research works.

Device	Variable	Density models (kg·m ⁻³)	R ² (%)	Species/product	Reference
BPV	ToF (µs)	$p=752.4-0.3201\cdot ToF$	16	Maritime p.	(6)
BPV	Edyn (MPa)	$p=634-0.0102\cdot Edyn$ (1)	18	Scots p.	(6)
Pilodyn	Depth (mm)	$p=711.2-13.9\cdot D$ (1)	80	Scots p.	(8)
IML Resi F300	Amplitude (%)	$p=385-21.02\cdot A$ (1)	85	Scots p.	(8)
SWRM	Force (kN)	$p=1000.0-2562\cdot F$ (2,36,11,F)	62	Scots p. (2)	(10)
Resistograph 3450-S	Area (%·cm ²)	$p=153+1.51\cdot Ar$	56		
Pilodyn	Depth (mm)	$p=744.6-22.2\cdot D$	35		
SWRM	Force (kN)	$p=289.9+109.7\cdot F$	49	Radiata, Scots, Salzmann p.	(11)
Pilodyn	Depth (mm)	$p=771.91-19.03\cdot D-97.01\cdot Zrad-63.19\cdot Zsco-0\cdot Zsal$	59	Radiata, Scots, Salzmann p.	(12)
SWRM	Force (kN)	$p=365.88+95.46\cdot F-81.47\cdot Zrad-38.53\cdot Zsco-0\cdot Zsal$	64		
IML Resi F300	Amplitude	$p=e^{0.32}\cdot (0.23\cdot logA)$	68	Salzmann p.	(13)
SylDuo	Transversal	$p=497.60+0.0385\cdot TV-75.53\cdot Zrad-57.07\cdot Zsco-24.50\cdot Zsal-0\cdot Zmar$	34		
MST	Velocity (m·s ⁻¹)	$p=467.02-0.0697\cdot TV-80.28\cdot Zrad-56.09\cdot Zsco+19.36\cdot Zsal+0\cdot Zmar$	34	Radiata, Scots Salzmann, maritime p.	(14)
Pilodyn	Depth (mm)	$p=131.07-20.54\cdot D-44.04\cdot Zrad-11.00\cdot Zsco+53.91\cdot Zsal+0\cdot Zmar$	61		
SWRM	Force (kN)	$p=389.29+89.61\cdot F-92.99\cdot Zrad-54.21\cdot Zsco+8.30\cdot Zsal+0\cdot Zmar$	67		
IML Resi E400	Amplitude	$p=326+19\cdot A$	44	Radiata, Scots p.	(15)
Resistograph 3450-S	Area (%·cm ²)	$p=394.797+0.7598\cdot Ar$	82	Salzmann, maritime, Scots p., sweet chestnut, European oak and walnut	(16)
SWRM	Force (kN)	$p=174.749+64.4308\cdot F$	74	Black poplar	(16)
Pilodyn	Depth (mm)	$p=700.193-15.9204\cdot D$	31		
SWRM	Force (kN)	$p=285.40+103.77\cdot F$	53	Radiata p.	(18)
Core drill bit Ø16 (10)	Core ρ (kg·m ⁻³)	$p=53.6357+0.850184\cdot CD$	88		
MST	Velocity (m·s ⁻¹)	$Ln(p)=-5.42+0.000492\cdot V+0.154\cdot Zp$	89	Particleboard and MDF	(19)
Pilodyn	Depth (mm)	$p=13.849+5778\cdot D$	74	18 species	(20)
Pilodyn	Depth (mm)	$p=622.932-11.6226\cdot D$	32		
SWRM	Force (kN)	$p=375.935+165.2801\cdot F$	33	Scots p.	(21)
Pilodyn + SWRM	D (mm)+F (kN)	$p=500.663-7.24375\cdot D+54.694\cdot F$	41		
SylDuo	Velocity (m·s ⁻¹)	$p=179.65+0.2193\cdot V$	97		
MST	Velocity (m·s ⁻¹)	$p=178.39+0.2439\cdot V$	98	Superpan boards	(22)
SWRM	Force (kN)	$p=341.74+227.458\cdot F$	90		
IML Resi-B 1280	Area/Length (bits)	$p=204.4+20.48\cdot F\cdot log$ (1)	70	Pine (2)	(23)
Core drill bit Ø7 (2)	Core ρ (kg·m ⁻³)	$p=122.62-0.6668\cdot CD$ (1)	48		
Pilodyn	Depth (mm)	$p=709-15.52\cdot D$	30		
SWRM	Force (kN)	$p=294+106.174\cdot F$	57	Radiata p.	(24)
Core drill bit Ø10 (10)	Core ρ (kg·m ⁻³)	$p=80+0.779\cdot CD$	80		
Core drill bit Ø16 (10)	Core ρ (kg·m ⁻³)	$p=87+0.827\cdot CD$	80		
Pilodyn	Depth (mm)	$p=689.73-10.324\cdot D-86.42\cdot Zrad-28.69\cdot Zsco+43.02\cdot Zsal+0\cdot Zmar$	56	Radiata, Scots Salzmann, maritime p.	(25)
SWRM	Force (kN)	$p=395.28+77.39\cdot F+66.63\cdot Zrad-13.21\cdot Zsco+41.99\cdot Zsal+0\cdot Zmar$	68		
Pilodyn	Depth (mm)	$p=776.09-17.376\cdot D$ (1)	51	Western red cedar, missanda, black poplar, sweet chestnut, oak, iroko, radiata, Scots, Salzmann, maritime p.	(26)
SWRM	Force (kN)	$p=445.483+94.63\cdot F$ (1)	53		
RML WoodEx	Chips Mass (g)	$p=97.59+428.66\cdot ChM$ (1)	96	Scots, Salzmann, Aleppo, A. pitch p.	(27)
IML Resi PD400	Amplitude (%)	$p=226.770+8.569\cdot A$	66		
IML Resi-B 1280	Resi ρ (kg·m ⁻³)	$p=421.9+0.3484\cdot CD$ (1)	39	Maritime p.	(28)
Core drill bit Ø7 (2)	Core ρ (kg·m ⁻³)	$p=0.9594\cdot CD$ (1)	67		
Pilodyn	Depth (mm)	$p=(-1280.08+4860.91\cdot SD)\cdot (2-10)$	86	Same 10 species Martínez 2016	(29)
Wood Pecker (10)	Depth (mm)	$p=e^{0.00878\cdot D+0.2070}$ (1)	75	Same 10 species Martínez 2016	(30)
Core drill bit Ø10 (10)	Core Mass (g)	$p=45+228\cdot CM$ (1)	98		
Pilodyn	Depth (mm)	$p=538-7.25\cdot D$	22		
Wood Pecker (10)	Depth (mm)	$p=562-5.70\cdot D$	33		
SWRM	Force (kN)	$p=349+64.69\cdot F$	53	Norway spruce (2)	(31)
Core drill bit Ø10 (10)	Core ρ (kg·m ⁻³)	$p=209+0.47\cdot CD$	84		
Core drill bit Ø16 (10)	Core ρ (kg·m ⁻³)	$p=270+0.34\cdot CD$	89		
RML WoodEx	Chips Mass (g)	$p=195+198.97\cdot ChM$	70		
Infrared	T 10 min (°C)	$p=-2510.93+73.0357\cdot T$ (1)	87	Saple, moshi, beech, cherry, pine, oak, tpe	(32)
Thermography	T 30 min (°C)	$p=-1705.75+73.3937\cdot T$ (1)	97		
RML WoodEx	Chips Mass (g)	$p=-30.79+363.13\cdot ChM$	84	Radiata, Scots Salzmann, maritime p.	(33)
Pilodyn	Chips ρ (kg·m ⁻³)	$p=90.39+0.871\cdot ChD$	81		
Wood Pecker (10)	Depth (mm)	$p=837.41-25.99\cdot D$	42		
SWRM	Force (kN)	$p=974.74-27.76\cdot F$	57	Salzmann p. (2)	(34)
RML WoodEx	Chips Mass (g)	$p=316.87+172\cdot F$	51		
		$p=35.94+343.06\cdot ChM$	76		

Zrad, Zsco, Zsal and Zmar are the constants for radiata, Scots, Salzmann and maritime pine, which are only equal to 1 for this species, for other species are 0; Zp is a constant for boards, which is equal to 1 for particleboards and 0 for MDF, (1)Small clear specimens,(2)Timber from existing structures,(3)Internal bit diameter (mm), (4)3 strikes, (5)5 strikes, (6)Martínez 1992, (7)Rubio 1997, (8)Palaia *et al.* 2000, (9)Mariño *et al.* 2002, (10)Casado *et al.* 2005, (11)Bobadilla *et al.* 2007, (12)Íñiguez-González 2007, (13)Vilches & Correal 2009, (14)Íñiguez-González *et al.* 2010, (15)Soto-Martínez 2010, (16)Acuña *et al.* 2011, (17)Casado *et al.* 2012, (18)Montón 2012, (19)Pérez-García 2012, (20)Cañas-Gutiérrez 2013, (21)Montero 2013, (22)Sevilla *et al.* 2013, (23)Morales-Conde *et al.* 2014, (24)Íñiguez-González *et al.* 2015^a, (25)Llana 2016, (26)Martínez 2016, (27)Camacho-Valero 2017, (28)Morales-Conde & Machado 2017, (29)Salamanca 2017, (30)Bobadilla *et al.* 2018, (31)Llana *et al.* 2018a, (32)López *et al.* 2018, (33)Martínez *et al.* 2018, (34)Osuna-Sequera *et al.* 2019b.

MC adjustment factors

Adjustment factors are important to achieve comparable results. Most research studies focus on MC influence. Palaia *et al.* (2000) showed that MC influence on ultrasound velocity measured on small clear specimens of Scots, maritime and Caribbean pitch pine varied with a power function. The higher the MC, the lower its influence. Rodríguez-Liñán and Rubio (1995), Llana *et al.* (2018b) and Llana *et al.* (2018c) reported

two different tendencies in which slopes were steeper below fiber saturation point (FSP) than above it, where MC influence is considered insignificant. Table 4 therefore presents adjustment factors to a reference MC value of 12 %, below FSP, as proposed for Spanish-grown species by Equation 1, Equation 2 and Equation 3:

$$Vel_{12\%MC} = \frac{Vel_{MC}}{\left[1 - k_{MC} \times (MC - 12)\right]} \tag{1}$$

$$Depth_{12\%MC} = \frac{Depth_{MC}}{\left[1 + k_{MC} \times (MC - 12)\right]} \tag{2}$$

$$Force_{12\%MC} = \frac{Force_{MC}}{\left[1 - k_{MC} \times (MC - 12)\right]} \tag{3}$$

Where: $Vel_{12\%MC}$ ($m \cdot s^{-1}$) obtained from ToF or longitudinal frequency at 12 % of MC, Vel_{MC} ($m \cdot s^{-1}$) at a given MC, $Depth_{12\%MC}$ (mm) obtained by the Pilodyn 6J Forest NPR instrument, $Depth_{MC}$ (mm) at a given MC, $Force_{12\%MC}$ (kN) obtained by the SWRM instrument, $Force_{MC}$ (kN) at a given MC, k_{MC} (as per unit) adjustment factors, which are listed in Table 4.

Table 4: MC adjustment factors (k_{MC}) in % for Spanish-grown species (below FSP).

Device	Variable corrected	k_{MC} (%)	Species	Reference
BPV	Velocity	0,70 ⁽¹⁾	Scots p.	(2)
Pilodyn	Depth	1,16	Radiata p.	(3)
SWRM	Force	3,20		
PLG Hitman HM200	Velocity	1,20	Sweet chestnut	(4)
SylDuo	Velocity	0,70 ⁽¹⁾	Scots p.	(5)
BPV		0,59 ⁽¹⁾		
Grindosonic MK5		1,06 ⁽¹⁾		
SylTrio	Velocity	0,48	Scots p.	(6)
MST		0,50		
PLG		0,65		
SylDuo USLab MST	Velocity	0,62	Radiata p.	(7)
		0,61	Scots p.	
		0,72	Salzmann p.	
		0,76	Maritime p.	
PLG MTG	Velocity	0,62	Radiata p.	
		0,63	Scots p.	
		0,73	Salzmann p.	
		0,76	Maritime p.	
Pilodyn	Depth	2,20	Radiata p.	(8)
		1,60	Scots p.	
		1,70	Salzmann p.	
		2,00	Maritime p.	
SWRM	Force	2,20	Radiata p.	
		2,80	Scots p.	
		2,50	Salzmann p.	
		2,10	Maritime p.	

⁽¹⁾ Small clear specimens, ⁽²⁾Rodríguez-Liñán and Rubio 1995, ⁽³⁾Calderón 2012, ⁽⁴⁾Vega 2013, ⁽⁵⁾Llana *et al.* 2014, ⁽⁶⁾Montero *et al.* 2015, ⁽⁷⁾Llana *et al.* 2018b, ⁽⁸⁾Llana *et al.* 2018c.

Visual grading

In order to add a new species to the visual grading standard it has to be characterized. Several research works in Spain during the past 30 years focused on this characterization. Fernández-Golfín *et al.* (1998) summarized the works done in the INIA Structural Timber Laboratory during several years for the characterization of radiata, Scots and maritime pine that led to the production of the first version of the UNE 56544 (1997) standard with two visual grades (ME-1, ME-2). Fernández-Golfín *et al.* (2001) published the works involved in adding Salzmann pine in the same standard. The results from Íñiguez-González *et al.* (2007b) made it possible to introduce the new visual grade MEG in the UNE 56544 (2007) for large cross-section timber (thickness > 70 mm). Fernández-Golfín *et al.* (2007) characterized southern blue gum for the first version of the hardwoods visual standard UNE 56546 (2007). Correal *et al.* (2013) and Vega *et al.* (2013) proposed visual grading criteria for structural sweet chestnut that were included in UNE 56546 (2013). Preliminary characterization works were also performed for other species that were not included in standards, such as Spanish juniper (Díez *et al.* 2006). Furthermore, five Spanish species appear in the EN 1912 (2012), and another one has been approved (Table 5). The latest allocations in EN 1912 (2012) were approved according to the works of Vega *et al.* (2013) and Hermoso *et al.* (2016). A new revision of the Spanish visual grading standards would be recommendable following the works of Montón *et al.* (2015), Llana *et al.* (2019) and the new version of European standard EN 14081:1 (2016). Several research studies were published comparing visual grading according to the Spanish standard UNE 56544 and the German standard DIN 4074-1, (Díez *et al.* 2000, Conde 2003, Arriaga *et al.* 2005b, Adell *et al.* 2008, Llana *et al.* 2019). In general, more pieces are rejected using the Spanish standard based on knot evaluation. A research work into the load carrying capacity of timber pieces from existing structures (Arriaga *et al.* 2005b) proposed a visual grading procedure limited to the main parameters (knots and slope of grain) in an attempt to simplify and adapt the procedure used in new timber to in-situ grading particularities. Other works studied the practically zero influence of some defects, such as fissures and waness, on mechanical properties (Arriaga *et al.* 2007, Esteban *et al.* 2010). Touza *et al.* (2013) proposed a new visual grading criterion for large cross-section American pitch pine specimens from existing structures, based on knots, grain slope and boring insect attacks. Arriaga *et al.* (2017b) showed that visual grading standards (designed for new sawn timber) lead to a high percentage of rejection in existing timber structures, and it is usually not possible to access all 4 faces. Furthermore, beam cross-section is not homogeneous (Osuna-Sequera *et al.* 2017). Vega *et al.* (2019a) found ineffective visual strength grading of 216 dry sweet chestnut small-diameter logs using EN 1927-1 (2008), EN 1927-2 (2008) and DIN 4074-2 (1958) standards.

Table 5: Correspondence between Spanish visual grades and strength classes according to the European standard EN 1912 (2012) and later approvals.

Species	(2)	Spanish visual grade				
		(3)			(4)	
		ME1	ME2	MEG	MEF	MEF-G
Salzmann pine	Strength class	C30	C18	C22		
Scots pine		C27	C18	C22		
Radiata pine		C24	C18	C20 ⁽¹⁾		
Maritime pine		C24	C18	-		
Southern blue gum					D40	-
Sweet chestnut					D27 ⁽¹⁾	D24 ⁽¹⁾

⁽¹⁾ Approved by CEN/TC124/WG2-TG1 in October 2014 and not yet included in ⁽²⁾EN 1912 (2012), ⁽³⁾UNE 56544 (2011),⁽⁴⁾ UNE 56546 (2013).

ME1 and ME2: Madera Estructural de 1ª y 2ª (structural timber 1st and 2nd quality)

MEG: Madera Estructural Gruesa escuadría (large cross-section structural timber)

MEF: Madera Estructural de Frondosas (hardwood structural timber)

MEF-G: Madera Estructural de Frondosas de Gruesa escuadría (hardwood large cross-section structural timber).

Final discussion

To summarise, 68 mechanical property estimation models from 29 research works were collected in Table

1 (acoustic techniques), 43 estimation models from 19 research works were included in Table 2 (vibration techniques) and 60 density estimation models from 29 research works were compiled in Table 3 (acoustic and probing techniques). These estimation models were developed from 1992 to 2019 in Spain. Most of these estimation models are valid for the same species, e.g. 24 different models to estimate MOE of the Scots pine (Spanish reference wood species) from ultrasound, stress waves and vibration devices are presented. If these different models are used to calculate MOE from common Spanish-grown Scots pine measurement values (acoustic velocity $5400 \text{ m} \cdot \text{s}^{-1}$, vibration velocity $4750 \text{ m} \cdot \text{s}^{-1}$ and density $510 \text{ kg} \cdot \text{m}^{-3}$, values from Llana (2016)), the mean MOE value obtained is 11734 MPa with a coefficient of variation of 12,6 % and standard deviation of 1474 MPa. No significant differences between MOE results of acoustic and vibration techniques were found. From the point of view of the authors, the results should be further studied to elucidate whether the recommended mechanical property estimation models for different NDT devices and species should be included in a new standard or at least in a protocol. However, if end-users develop their own models, these can be used instead of the standardized models. Furthermore, several MC adjustment factors for Spanish-grown species are presented in Table 4 that would be also included in a new standard or protocol. NDT measurement procedures should be unified, e.g. Osuna-Sequera *et al.* (2019b) concluded that in order to increase the accuracy of density estimation using probing techniques, from three to five measurements in at least two different cross-section areas including the middle point are needed. This should be included in UNE 41809 (2014) as a measurement recommendation.

Better knowledge of the research undertaken should help to prevent overlapping between research groups' works and promote cooperation between them. Some research works presented here are almost unknown: e.g. several interesting and useful results were only published as final degree projects. In 2016 a net of Spanish-timber research groups was created under the name LIGNOMAD to find common objectives and promote collaboration. Research groups should identify potential research objectives, find other research groups with similar objectives and apply together for funding. Furthermore, useful information from previous research works compiled in this review paper can be helpful. E.g. a potential new topic is the reuse and recycling of recovered timber. In this review it was reported that at least one research group in Spain is working on this topic, and several estimation models for timber from existing structures were developed and visual grading criteria for timber from existing structures were proposed. Finally, apart from visual grading, NDT techniques are not used by the Spanish industry for grading purposes, while they are commonly used in most European countries. Therefore, closer collaboration between research groups and industry is needed to implement NDT for grading.

Future milestones

The main milestones that are expected to be achieved in the near future, given that some Spanish research groups are currently working on them, are: (1) a NDT grading standard for new structural sawn timber, (2) further implementation of NDT in Spanish timber industry, (3) assessment protocol for existing timber structures, including special guidelines for visual grading and for NDT use, (4) models for estimating properties in existing timber structures.

CONCLUSIONS

Most Spanish research works focus on NDT portable devices which can be used both in new sawn and round timber grading and to assess existing structures. These techniques are not used in practice in the Spanish industry for grading. However, they are frequently used to assess timber structures. Several statistical linear models for the estimation of mechanical properties using different NDT devices (68 models based on acoustic techniques, 43 based on vibration and 60 for density estimation) were developed in Spain from 1992 to 2019, most of them for new sawn timber.

The results obtained are very variable because the methods used are not exactly the same (size of the pieces, wood free of defects vs. structural size timber and the arrangement of measuring equipment, etc.). It is therefore difficult to extrapolate the use of a model for general application. It is very important that in the future different research groups use unified procedures (MC adjustment factors, number of measurements and the way to carry out them) to enhance the capacity of these techniques.

Although many research works have been published in Spanish and in Spanish conferences and work-

shops, fortunately in recent years more research has been published in English and in scientific journals, allowing international dissemination. Some useful research works presented here are almost unknown. Information from previous research works compiled in this review paper should help research groups to identify potential research objectives, find other research groups with similar objectives and avoid overlapping works.

ACKNOWLEDGMENTS

Ministerio de Economía y Competitividad (Spanish Ministry of Economy and Competitiveness). Projects: BIA 2014-55089-P; BIA 2010-18858; BIA 2006-14272; AGL 2002-00813; PAT 91-0152; PAT 90-0224. CON-09-070; CC02-0031; CON03-001; AGF 99-0176; AGL2004-01598; SC00-043; SC96-045-C2-2. VA047A08. 09MRU004CT. PSING-10-11.

The authors would like to thank Dr. Abel Vega from CETEMAS and Dr. Joaquín Montón from UPC for supplying photographs, together with the laboratory technicians whose work is essential in all research.

REFERENCES

Abián, M.A.; Segura, G. 2016. Evaluación del estado estructural de la madera después de incendios mediante técnicas no destructivas (Assessment of fire-damaged structural timber by non-destructive testing). In Proceedings of the IV Fire Engineering Conference. Valencia, Spain. 4 p.

Acuña, L.; Díez, M.R.; Martín, L.; Casado, M.; Basterra, L.A.; Ramón, G.; Relea, E. 2007. La técnica de transmisión ultrasónica aplicada a la madera estructural (Ultrasonic transmission technique applied to structural lumber). In Proceedings of the 11º Congreso Español de Ensayos No Destructivos. Gijón, Spain, pp. 91-102.

Acuña, L.; Basterra, L.A.; Casado, M.; López, G.; Ramón, G.; Relea, E.; Martínez, C.; González, A. 2011. Aplicación del resistógrafo a la obtención de la densidad y la diferenciación de especies de madera (Application of resistograph to obtain the density and to differentiate wood species). *Mater Construcc* 61(303): 451-464. <https://doi.org/10.3989/mc.2010.57610>.

Adell, F.J.; Hermoso, E.; Arriaga, F.; Richter, C. 2008. Comparison of the Spanish visual strength grading standard for structural sawn timber (UNE 56544) with the German one (DIN 4074) for Scots pine (*Pinus sylvestris* L.) from Germany. *Holz Roh Werkst* 66: 253-258. <https://doi.org/10.1007/s00107-008-0241-9>.

Aira, J.R.; Villanueva, J.L.; Lafuente, E. 2019. Visual and machine grading of small diameter machined round *Pinus sylvestris* and *Pinus nigra* subsp. *Salzmannii* wood from mature Spanish forests. *Mater Struct* 52: 32. <https://doi.org/10.1617/s11527-019-1330-4>.

Arce-Blanco, M. 2017. Estudio de las bóvedas encamionadas en Madrid capital y análisis de su comportamiento estructural (Plank timber arches study in Madrid capital and analysis of structural behavior). Ph.D. Thesis, UPM, Madrid, Spain. <https://doi.org/10.20868/UPM.thesis.48247>.

Argüelles, R.; Arriaga, F. 1986. Norma de cálculo de estructuras de madera. (Timber structures design standard). AITIM: Madrid, Spain. pp. 80-89.

Arriaga, F.; García, L.; Gebremedhin, K.G.; Peraza, F. 1992. Grading and load carrying capacity of old timber beams. In Proceedings of the International Summer Meeting, American Society of Agricultural Engineers. Charlotte, NC, USA. 25 p.

Arriaga, F.; Íñiguez-González, G.; Esteban, M. 2005a. Assessment of strength and stiffness properties using longitudinal stress wave on structural gross cross section timber of radiate pine (*Pinus radiata* D. Don). In Proceedings of the 14th International Symposium on Nondestructive Testing of Wood. Hannover, Germany. pp. 103-109.

Arriaga, F.; Esteban, M.; Relea, E. 2005b. Evaluación de la capacidad portante de piezas de gruesa escuadría de madera de conífera en estructuras existentes (Evaluation of the load carrying capacity of large cross section coniferous timber in standing structures). *Mater Construcc* 55(280): 43-52. <https://doi.org/10.3989/mc.2005.v55.i280.205>.

Arriaga, F.; Íñiguez-González, G.; Esteban, M.; Fernández-Golfin, J.I. 2006. Structural Tali timber (*Erythrophleum ivorense* A. Chev., *Erythrophleum suaveolens* Brenan.): assessment of strength and stiffness properties using visual and ultrasonic methods. *Holz Roh Werkst* 64: 357-362. <https://doi.org/10.1007/s00107-006-0100-5>.

Arriaga, F.; Esteban, M.; Argüelles, R.; Bobadilla, I.; Íñiguez-González, G. 2007. Efecto de las gemas en la resistencia a flexión de piezas enterizas de madera (The effect of waness on the bending strength of solid timber beams). *Mater Construcc* 57(288): 61-76. <http://materconstrucc.revistas.csic.es/index.php/materconstrucc/article/view/65/78>.

Arriaga, F.; Íñiguez-González, G.; Esteban, M.; Bobadilla, I. 2009. Proposal of a methodology for the assessment of existing timber structures in Spain. In Proceedings of the 16th International Symposium on Nondestructive Testing of Wood. Beijing, China. pp. 145-151.

Arriaga, F.; Íñiguez-González, G.; Esteban, M.; Divós, F. 2012. Vibration method for grading of large cross-section coniferous timber species. *Holzforschung* 66: 381-387. <https://doi.org/10.1515/hf.2011.167>

Arriaga, F.; Montón, J.; Segué, E.; Íñiguez-González, G. 2014. Determination of the mechanical properties of radiata pine timber by means of longitudinal and transverse vibration methods. *Holzforschung* 68: 299-305. <https://doi.org/10.1515/hf-2013-0087>.

Arriaga, F.; Llana, D.F.; Esteban, M.; Íñiguez-González, G. 2017a. Influence of length and sensor positioning on acoustic time-of flight (ToF) measurement in structural timber. *Holzforschung* 71: 713-723. <https://doi.org/10.1515/hf-2016-0214>.

Arriaga, F.; Íñiguez-González, G.; Llana, D.F.; Bobadilla, I.; Esteban, M. 2017b. Procedural considerations for the assessment of mechanical properties in existing timber structures. In Proceedings of the 20th International Nondestructive Testing and Evaluation of Wood Symposium. Madison, WI, USA. pp. 204-212.

Arriaga, F.; Montón, J.; Bobadilla, I.; Llana, D.F. 2019. Influence of length on acoustic time-of-flight (ToF) measurement in built-in structures of Norway spruce timber. *Holzforschung* 73(4): 339-352. <https://doi.org/10.1515/hf-2018-0122>.

Atienza-Conejo, L. 2012. Diagnóstico de estructuras atacadas por insectos xilófagos mediante ultrasonidos usando la técnica de pulso eco (Timber assessment of structures with xylophagous insect attacks by pulse-echo ultrasound technique). Final Project Degree. UPC, Barcelona, Spain. <https://upcommons.upc.edu/handle/2099.1/14443>.

Balmori, J.A.; Acuña, L.; Basterra, L.A. 2016. Estudio de la influencia de la dirección de la fibra en la velocidad de propagación de ultrasonidos (Fakopp) en madera estructural de *Pinus sylvestris* L. y *Pinus radiata* D. Don. (Grain angle influence on ultrasound velocity (Fakopp) on *Pinus sylvestris* L. and *Pinus radiata* D. Don structural timber). In Proceedings of the Congreso Euro-Americano REHABEND 2016. Burgos, Spain. pp. 746-755.

Baño, V.; Santos, J.C.; Vivas, J.; Rodríguez, S.; Vega, A.; Crews, K. 2011. A study of the influence of different types of timber footbridges on the vibrational natural frequency. In Proceedings of the 17th International Nondestructive Testing and Evaluation of Wood Symposium. Sopron, Hungary. pp. 531-537.

Basterra, L.A.; Acuña, L.; Casado, M.; Ramón, G.; López, G. 2009. Diagnóstico y análisis de estructuras de madera mediante técnicas no destructivas: aplicación a la plaza mayor de Chinchón (Madrid) (Diagnosis and assessment of timber structures using nondestructive techniques: application to the Plaza Mayor in Chinchón (Madrid)). *Inf Constr* 61(516): 21-36. <https://doi.org/10.3989/ic.09.016>.

Bobadilla, I.; Íñiguez-González, G.; Esteban, M.; Arriaga, F.; Casas, L. 2007. Density estimation by screw withdrawal resistance and probing in structural sawn coniferous timber. In Proceedings of the 15th International Symposium on Nondestructive Testing of Wood. September 10-12. Duluth, MN, USA. pp. 247-251.

Bobadilla, I.; Martínez, R.D.; Calvo, J.; Arriaga, F.; Íñiguez-González, G. 2013. First steps in wood density estimation using a conventional drill. In Proceedings of the 18th International Nondestructive Testing and Evaluation of Wood Symposium. September 24-27. Madison, WI, USA. pp. 112-118.

Bobadilla, I.; Martínez, R.D.; Esteban, M.; Llana, D.F. 2018. Estimation of wood density by the core drilling technique. *Holzforschung* 72(12): 1051-1056. <https://doi.org/10.1515/hf-2018-0036>.

Broto, M.; Villanueva, J.L.; Lafuente, E.; Rodríguez, F. 2007. Evaluación de la resistencia por frecuencia de resonancia. Un caso práctico (Strength evaluation from resonance frequency: a case study). In Proceedings of the III Congreso Iberoamericano de Productos Forestales. Buenos Aires, Argentina. 1p.

Bucur, V.; Navarrete, A.; Troya, M.T.; Sánchez, E.; Garros, S.; Díez, M.R. 1993. Fungi decay in wood by combined nondestructive testings. In Proceedings of the Ultrasonics International 93 Conference. Vienna, Austria. pp. 287-290.

Cáceres-Hidalgo, E. 2016. Caracterización físico-mecánica de la madera de *Paulownia elongata* (Physico-mechanical characterization of *Paulownia elongata* timber). Final Project Master Degree. UVa, Palencia, Spain. <http://uvadoc.uva.es/handle/10324/18787>.

Calderón, L. 2012. Estudio sobre la influencia del contenido de humedad de la madera en ensayos no destructivos para *Pinus nigra* Arn., *Pinus radiata* D. Don y *Pinus sylvestris* L. (Study of wood moisture content influence on nondestructive measurements on *Pinus nigra* Arn., *Pinus radiata* D. Don and *Pinus sylvestris* L.). Final Project Degree. UPM, Madrid, Spain. <http://oa.upm.es/14396/>.

Camacho-Valero, J. 2017. Evaluación no destructiva de madera antigua y patrimonial usada estructuralmente (Nondestructive evaluation of structural old heritage timber). Final Project Degree. UPV, Valencia, Spain. <https://riunet.upv.es/handle/10251/86871>.

Cañas-Gutiérrez, I. 2013. Capacidad de predicción del penetrómetro “Pilodyn” en la determinación de la densidad de la madera (Timber density estimation by Pilodyn penetrometer). Final Project Degree. UVa, Palencia, Spain. <http://uvadoc.uva.es/handle/10324/4682>.

Capuz, R.; Díez, M.R.; Botelho, J.; San-Valero, E. 2007. Aplicación de métodos de ensayo no destructivos a vigas del forjado del consulado del mar de la Lonja de los Mercaderes de Valencia (NDT evaluation of deck beams in “La Lonja de Mercaderes” in Valencia). In Proceedings of the III Congreso Iberoamericano de Productos Forestales. Buenos Aires, Argentina. 6 p.

Carballo, J.; Hermoso, E.; Fernández-Golfín, J.I. 2007. Influencia del tamaño en la predicción del módulo de elasticidad de vigas de madera de *Pinus pinaster* con técnicas vibratorias (Influence of the size for elasticity modulus prediction using vibration techniques over *Pinus pinaster* timber). In Proceedings of the II Jornadas de investigación en construcción. Instituto de ciencias de la construcción Eduardo Torroja. Madrid, Spain. 10 p.

Carballo, J.; Hermoso, E.; Díez, M.R. 2009a. Ensayos no destructivos sobre madera estructural. Una revisión de 30 años en España. (Non-destructive testing on structural timber. A review of last 30 years in Spain). *Revista forestal (Costa Rica)* 6(17): 1-16. <https://revistas.tec.ac.cr/index.php/kuru/article/view/387>.

Carballo, J.; Hermoso, E.; Fernández-Golfín, J.I. 2009b. Comparación de la evaluación y clasificación mecánica del *Pinus pinaster* Ait. con dos equipos de ultrasonidos (Comparison of evaluation and mechanical grading of *Pinus pinaster* Ait. by two ultrasound devices). In Proceedings of the 5º Congreso Forestal Español. Avila, Spain. 12 p.

Casado, M.; Basterra, L.A.; Acuña, L.; Pinazo, O.; Martínez, C.; Relea, E.; Barranco, I.; Ramón, G. 2005. Determinación de la capacidad resistente mediante métodos no destructivos. Aplicación en viguetas de forjado de un edificio singular (Determination of resistance by non destructive testing applied to structural timber joists from a singular building). In Proceedings of the IV Congreso Forestal Español. Zaragoza, Spain. 7 p.

Casado, M.; Acuña, L.; Vecilla, D.; Basterra, L.A.; Pando, V.; Relea, E. 2007. Determinación de la capacidad resistente de madera estructural de *Pinus sylvestris* mediante PLG (Determination of bending strength of structural timber of *Pinus sylvestris* by PLG). In Proceedings of the 11º Congreso Español de Ensayos No Destructivos. Gijón, Spain. 10 p.

Casado, M.; Acuña, L.; Basterra, L.A.; Relea, E. 2008. Clasificación de madera estructural de *Pinus pinaster* mediante técnicas vibratorias (Grading of *Pinus pinaster* structural timber by vibration techniques). In Proceedings of the II Jornadas de Investigación en Construcción. Instituto de Ciencias de la Construcción Eduardo Torroja. Madrid, Spain. 9 p.

Casado, M.; Escudero, I.; Acuña, L.; Vecilla, D.; Basterra, L.A.; Ramón, G.; López, G.; Relea, E. 2009. Técnicas vibratorias aplicadas a madera estructural de *Populus x euramericana* (Application of vibration techniques to structural timber of *Populus x euramericana*). In Proceedings of the 5º Congreso Forestal Español. Avila, Spain. 14 p.

Casado, M.; Acuña, L.; Vecilla, D.; Relea, E.; Basterra, L.A.; Ramón, G.; López, G. 2010. The influence of size in predicting the elastic modulus of *Populus x euramericana* timber using vibration techniques. In *Structures and Architecture*. Taylor & Francis Group, London, UK. pp. 2025-2032. <http://maderas.uva.es/files/2019/03/2010-Casado-et-al-The-influence-of-size-MOE-Populus-PLG.pdf>.

Casado, M.; Acuña, L.; Basterra, L.A.; Ramón, G.; Vecilla, D. 2012. Grading of structural timber of *Populus x euroamericana* clone I-214. *Holzforschung* 66(5): 633-638. <https://doi.org/10.1515/hf-2011-0153>.

Casado, M.; Acuña, L.; Basterra, L.A.; Heredero, S.; SanMartín, R. 2013. Estimación de la calidad de la madera en rollo de *Populus x euramericana* mediante ultrasonidos (Estimation of round timber quality of *Populus x euramericana* by ultrasound). In Proceedings of the 6º Congreso Forestal Español. Vitoria, Spain. 11p.

Castro-Triguero, R.; García-Macías, E.; Saavedra-Flores, E.; Friswell, M.I.; Gallego, R. 2017. Multi-scale model updating of a timber footbridge using experimental vibration data. *Eng Computation* 34(3): 754-780. <https://doi.org/10.1108/EC-09-2015-0284>.

Conde, M. 2003. Caracterización de la madera estructural de *Pinus nigra* Subsp. *Salzmannii*. (Characterization of structural timber from *Pinus nigra* Ssp. *Salzmannii*). Ph.D. Thesis, UPM, Madrid, Spain.

Conde, M.; Fernández-Golfín, J.I.; Hermoso, E. 2007. Mejora de la predicción de la resistencia y rigidez de la madera estructural con el método de ultrasonidos combinado con parámetros de clasificación visual (Improving the prediction of strength and rigidity of structural timber by combining ultrasound techniques with visual grading parameters). *Mater Construcc* 57(288): 49-59. <http://materconstrucc.revistas.csic.es/index.php/materconstrucc/article/view/64/77>.

Correal, E.; Vilches, M.; Iglesias, C. 2013. Clasificación visual de la madera estructural de *Castanea sativa* del Sistema Mediterráneo Catalán (Visual grading for structural sawn timber of *Castanea sativa* from Catalan Mediterranean source). In Proceedings of the 6º Congreso Forestal Español. Vitoria, Spain. 12p.

Crespo, J.; Aira, J.R.; Vázquez, C.; Guaita, M. 2017. Comparative analysis of the elastic constants measured via conventional, ultrasound, and 3-D digital image correlation methods in *Eucalyptus globulus* Labill. *BioResources* 12(2): 3728-3743. <https://doi.org/10.15376/biores.12.2.3728-3743>.

Crespo-de-Antonio, M.; Luengas-Carreño, D.; Sánchez-Beitia, S. 2016. Applications of the hole-drilling technique in timber structures. Case studies. In Proceedings of the 10th International Conference on Structural Analysis of Historical Constructions. Leuven, Belgium. pp. 776-781.

Díez, M.R.; Conde, M.; Fernández-Gofín, J.I.; Roskopf, S. 2000. Clasificación visual de madera estructural de pino laricio (*Pinus nigra* Arn.): Comparación de resultados usando las normas UNE 56544 y DIN 4074 (Visual grading of structural timber of Salzmann pine (*Pinus nigra* Arn.): Comparison of results using standards UNE 56544 and DIN 4074). *Inv Agrar-Sist Rec F* 9(2): 375-380. <https://recyt.fecyt.es/index.php/IA/article/view/2630/2007>.

Díez, M.R.; Cabrero-Rojo, J.C.; García-Lombardero, R. 2006. Caracterización de la sabina albar con piezas de tamaño casi estructural. Intentos preliminares (Spanish juniper characterization of almost structural size timber. Preliminary results). In Proceedings of the III Coloquio Internacional sobre Sabinas y Enebrales (género *Juniperus*): Ecología y gestión forestal sostenible. Soria, Spain. 5 p.

DIN. 1958. *Bauholz für Holzbauteile; Gütebedingungen für Baurundholz (Nadelholz)* (Building Timber for Wood Building Components; Quality Conditions for Building Logs (Softwood)). DIN 4074-2. 1958. Nor-

menausschuss Holzwirtschaft und Möbel (NHM): Berlin, Germany.

DIN. 2012. *Sortierung von Holz nach der Tragfähigkeit - Teil 1: Nadelschnittholz* (Strength grading of wood - Part 1: Coniferous sawn timber). DIN 4074-1. 2012. Normenausschuss Holzwirtschaft und Möbel (NHM): Berlin, Germany.

Esteban, M. 2003. Determinación de la capacidad resistente de la madera estructural de gran escuadría y su aplicación en estructuras existentes de madera de conífera (Determination of the load carrying capacity of large cross-section structural coniferous timber in existing structures). Ph.D. Thesis, UPM, Madrid, Spain. <http://oa.upm.es/1404/>.

Esteban, M.; Bobadilla, I.; Arriaga, F.; Íñiguez-González, G.; García, H. 2009. NDT applied to estimate the mechanical properties of the timber of an ancient structure in Valsaín, Segovia (Spain). In Proceedings of the 16th International Symposium on Nondestructive Testing of Wood. Beijing, China. pp. 152-157.

Esteban, M.; Arriaga, F.; Íñiguez-González, G.; Bobadilla, I.; Mateo, R. 2010. Influencia de las fendas en la resistencia de la madera estructural (The effect of fissures on the strength of structural timber). *Mater Construcc* 60(299): 115-132. <https://doi.org/10.3989/mc.2010.48208>.

European Committee of Standardization. CEN. 2008. Qualitative classification of softwood round timber - Part 1: Spruces and firs. EN 1927-1. 2008. European Committee of Standardization (CEN): Brussels, Belgium.

European Committee of Standardization. CEN. 2008. Qualitative classification of softwood round timber - Part 2: Pines. EN 1927-2. 2008. European Committee of Standardization (CEN): Brussels, Belgium.

European Committee of Standardization. CEN. 2010. Timber structures – Strength graded structural timber with rectangular cross section - Part 2: Machine grading; additional requirements for initial type testing. EN 14081-2. 2010. European Committee of Standardization (CEN): Brussels, Belgium.

European Committee of Standardization. CEN. 2012. Structural timber. Strength classes. Assignment of visual grades and species. EN 1912. 2012. European Committee of Standardization (CEN): Brussels, Belgium.

European Committee of Standardization. CEN. 2016. Structural timber. Strength classes. EN 338. 2016. European Committee of Standardization (CEN): Brussels, Belgium.

European Committee of Standardization. CEN. 2016. Timber structures - Strength graded structural timber with rectangular cross section - Part 1: General requirements. EN 14081-1. 2016. European Committee of Standardization (CEN): Brussels, Belgium.

Fernández-Golfin, J.I.; Díez, M.R.; Gutiérrez-Oliva, A. 1998. Caracterización mecánica de la madera aserrada de uso estructural, clasificada visualmente de acuerdo con la norma UNE56544 (Mechanical characterization of sawn timber for structural use, graded visually in accordance with Spanish standard UNE56544). *Mater Construcc* 48(252): 45-59. <http://materconstrucc.revistas.csic.es/index.php/materconstrucc/article/view/463/511>.

Fernández-Golfin, J.I.; Díez, M.R.; Baonza, M.V.; Gutiérrez-Oliva, A.; Hermoso, E.; Conde, M.; Van den Eynde, V. 2001. Caracterización de la calidad y las propiedades de la madera de Pino laricio (*Pinus nigra* Arn. *salzmannii*) (Quality and properties characterization of Salzmann pine (*Pinus nigra* Arn. *salzmannii*) timber). *Inv Agrar-Sist Rec F* 10(2): 311-331. <http://www.inia.es/IASPF/2001/vol10-2/ferna.PDF>.

Fernández-Golfin, J.I.; Díez, M.R.; Hermoso, E.; Baso, C.; Casas, J.M.; González, O. 2007. Caracterización de la madera de *Eucalyptus globulus* para uso estructural (Characteristics of eucalyptus wood for structural purposes). *CIDEU* 4: 91-100. <https://dialnet.unirioja.es/descarga/articulo/2723431.pdf>.

Galvañ, V.; Palaia, L.; Cervera, F.; Monzo, V. 1994. Strength estimation of decayed timber in old buildings by means of ultrasonic devices. In Proceedings of the 1st European Symposium on Nondestructive Evaluation of Wood. Sopron, Hungary. pp. 156-170.

García-de-Ceca, J.L.; Hermoso, E.; Mateo, R.; Íñiguez-González, G. 2013. Neural network models for

the establishment of a structural stress grading methodology using nondestructive techniques. In Proceedings of the 18th International Nondestructive Testing and Evaluation of Wood Symposium. Madison, WI, USA. p. 808.

García-Esteban, L.; García-Fernández, F.; Palacios, P. 2009. MOE prediction in *Abies pinsapo* Boiss. timber: Application of an artificial neural network using non-destructive testing. *Comput Struct* 87: 1360-1365. <https://doi.org/10.1016/j.compstruc.2009.08.010>.

García-Iruela, A.; García-Fernández, F.; García-Esteban, L.; Palacios, P.; Simón, C.; Arriaga, F. 2016. Comparison of modelling using regression techniques and an artificial neural network for obtaining the static modulus of elasticity of *Pinus radiata* D. Don. timber by ultrasound. *Compos Part B-Eng* 96: 112-118. <https://doi.org/10.1016/j.compositesb.2016.04.036>.

González-Sanz, M. 2012. Estudio sobre el estado de conservación de la cubierta del martinete de Navafría (Segovia) (Assessment of roof structure of Navafría forge (Segovia)). Final Project Degree. UPM, Madrid, Spain. <http://oa.upm.es/36345/>.

Gutiérrez-Sánchez, R.; Basterra, L.A.; Acuña, L.; Casado, M.; Morillas, L.; López, G.; Balmori, J.A. 2019. Sistema y procedimiento de medición sónico para diagnóstico de elementos estructurales de madera. WO2018178482. España. <https://patentscope.wipo.int/search/es/detail.jsf?docId=WO2018178482>.

Hermoso, E. 2001. Caracterización mecánica de la madera estructural de *Pinus sylvestris* L. (Mechanical characterization of *Pinus sylvestris* L. structural timber). Ph.D. Thesis, UPM, Madrid, Spain. <http://oa.upm.es/644/>.

Hermoso, E.; Díez, M.R.; Fernández-Golfín, J.I.; Mier, R. 2002. Calidad de la madera aserrada mediante evaluación no destructiva con ultrasonidos (Quality assessment of sawn timber by ultrasound non-destructive testing). In Proceedings of the II Congreso Nacional de la Madera. Segovia, Spain. 13 p.

Hermoso, E.; Fernández-Golfín, J.I.; Díez, M.R. 2003. Evaluación de la clasificación resistente de la madera estructural mediante ultrasonidos (Evaluation of structural timber strength grading by ultrasound). In Proceedings of the the 10^o Congreso Nacional de Ensayos No Destructivos. Cartagena, Spain. 9 p.

Hermoso, E.; Fernández-Golfín, J.I.; Díez, M.R.; Mier, R. 2007. Aplicación de los ultrasonidos a la evaluación de las propiedades mecánicas de la madera en rollo de pequeño diámetro (Ultrasound application to evaluation of small round timber mechanic properties). *Inf Constr* 59(506): 87-95. <http://informesdelaconstruccion.revistas.csic.es/index.php/informesdelaconstruccion/article/view/511/586>.

Hermoso, E.; Mateo, R.; Íñiguez-González, G.; Montón, J.; Arriaga, F. 2016. Visual grading and structural properties assessment of large cross-section *Pinus radiata* D. Don timber. *BioResources* 11(2): 5312-5321. <https://doi.org/10.15376/biores.11.2.5312-5321>.

Hillig, E.; Bobadilla, I.; Gonçalves, R.; Llana, D.F. 2018. The influence of wood polymer composite (WPC) specimen composition and dimensions on wave propagation. *Eur J Wood Prod* 76(4): 1153-1164. <https://doi.org/10.1007/s00107-018-1309-9>.

Íñiguez-González, G. 2007. Clasificación mediante técnicas no destructivas y evaluación de las propiedades mecánicas de la madera aserrada de coníferas de gran escuadría para uso estructural. (Grading by non destructive techniques and assessment of the mechanical properties of large cross section coniferous sawn timber for structural use). Ph.D. Thesis, UPM, Madrid, Spain. <http://oa.upm.es/415/>.

Íñiguez-González, G.; Esteban, M.; Arriaga, F.; Bobadilla, I.; Gil, M.C. 2007a. Influence of specimen length on ultrasound wave velocity. In Proceedings of the 15th International Symposium on Nondestructive Testing of Wood. Duluth, MN, USA. pp. 155-159.

Íñiguez-González, G.; Arriaga, F.; Barrett, J.D.; Esteban, M. 2007b. Visual grading of large structural coniferous sawn timber according to Spanish standard UNE 56544. *Forest Prod J* 57(10): 45-50.

Íñiguez-González, G.; Martínez, R.D.; Bobadilla, I.; Arriaga, F.; Esteban, M. 2009. Mechanical properties assessment of structural coniferous timber by means of parallel and perpendicular to the grain wave velocity. In Proceedings of the 16th International Symposium on Nondestructive Testing of Wood. Beijing,

China. pp. 79-84.

Íñiguez-González, G.; Arriaga, F.; Esteban, M.; Bobadilla, I.; González, C.; Martínez, R.D. 2010. In situ non-destructive density estimation for the assessment of existing timber structures. In Proceedings of the World Conference on Timber Engineering (WCTE). Riva di Garda, Italy. 8 p.

Íñiguez-González, G.; Montón, J.; Arriaga, F.; Segué, E. 2015a. In-situ assessment of structural timber density using non-destructive and semi-destructive testing. *BioResources* 10(2): 2256-2265. <https://biore-sources.cnr.ncsu.edu/resources/in-situ-assessment-of-structural-timber-density-using-non-destructive-and-se-mi-destructive-testing/>.

Íñiguez-González, G.; Arriaga, F.; Esteban, M.; Llana, D.F. 2015b. Reference conditions and modification factors for the standardization of nondestructive variables used in the evaluation of existing structures. *Constr Build Mater* 101:1166-1171. <https://doi.org/10.1016/j.conbuildmat.2015.05.128>.

Íñiguez-González, G.; Arriaga, F.; Osuna-Sequera, C.; Esteban, M.; Ridley-Ellis, D. 2019. Nondestructive measurements in reclaimed timber from existing structures. In Proceedings of the 21st International Nondestructive Testing and Evaluation of Wood Symposium. Freiburg im Breisgau, BW, Germany. pp. 462-472.

Llana, D.F.; Sanabria, S.J.; Íñiguez-González, G.; Arriaga, F.; Niemz, P. 2013. Experimental and numerical investigation of effect of sawn timber dimensions in ultrasonic velocity measurements for Spanish softwoods. In Proceedings of the 18th International Nondestructive Testing and Evaluation of Wood Symposium. Madison, WI, USA. p. 710.

Llana, D.F.; Íñiguez-González, G.; Arriaga, F.; Niemz, P. 2014. Influence of temperature and moisture content on non-destructive measurements in Scots pine wood. *Wood Research* 59(5): 769-780. <http://www.woodresearch.sk/wr/201405/06.pdf>.

Llana, D.F. 2016. Influencia de factores físicos y geométricos en la clasificación estructural de la madera mediante técnicas no destructivas (The influence of physical and geometrical factors on timber stress-grading by non-destructive techniques). Ph.D. Thesis, UPM, Madrid, Spain. <https://doi.org/10.20868/UPM.the-sis.43696>.

Llana, D.F.; Íñiguez-González, G.; Arriaga, F.; Wang, X. 2016. Time-of-flight adjustment procedure for acoustic measurements in structural timber. *BioResources* 11(2): 3303-3317. <https://doi.org/10.15376/biores.11.2.3303-3317>.

Llana, D.F.; Íñiguez-González, G.; Montón, J.; Arriaga, F. 2018a. In-situ density estimation by four nondestructive techniques on Norway spruce from built-in wood structures. *Holzforschung* 72(10): 871-879. <https://doi.org/10.1515/hf-2018-0027>.

Llana, D.F.; Íñiguez-González, G.; Martínez, R.D.; Arriaga, F. 2018b. Influence of timber moisture content on wave time-of-flight and longitudinal natural frequency in coniferous species for different instruments. *Holzforschung* 72(5): 405-411. <https://doi.org/10.1515/hf-2017-0113>.

Llana, D.F.; Hermoso, E.; Bobadilla, I.; Íñiguez-González, G. 2018c. Influence of moisture content on the results of penetration and withdrawal resistance measurements on softwoods. *Holzforschung* 72(7): 549-555. <https://doi.org/10.1515/hf-2017-0133>.

Llana, D.F.; Arriaga, F.; Esteban, M.; Íñiguez-González, G. 2019. Comparison between wet and dry timber visual strength grading according to the Spanish (UNE 56544) and German (DIN 4074-1) standards. *Mater Construcc* 69(336): e205. <https://doi.org/10.3989/mc.2019.03319>.

López, G.; Basterra, L.A.; Acuña, L. 2018. Infrared thermography for wood density estimation. *Infrared Phys Techn* 89: 242-246. <https://doi.org/10.1016/j.infrared.2018.01.015>.

Lozano, A.; Guaita, M.; Lorenzo, D.; Benito, J. 2013. Investigation about the decay of the timber structure of an ancient wine cellar in La Rioja (Spain) and sanitation proposal. *Adv Mater Res-Switz* 778: 976-982. <https://doi.org/10.4028/www.scientific.net/AMR.778.976>.

Mariño, R.A.; Fernández, M.E.; Fernández-Rodríguez, C. 2002. Análisis comparativo de la densidad de la madera de *Pinus sylvestris* L. mediante la utilización del resistógrafo (Comparative analysis of *Pinus sylvestris* L. wood density using resistograph). *Revista CIS-Madera* 9: 60-70.

Mariño, R.A.; Fernández, M.E.; Fernández-Rodríguez, C.; Méndez, M. 2010. Detection of pith location in chestnut lumber (*Castanea sativa* Mill.) by means of acoustic tomography and longitudinal stress-wave velocity. *Eur J Wood Prod* 68: 197-206. <https://doi.org/10.1007/s00107-009-0366-5>.

Martín, M.T. 1994. Some nondestructive methods to determine physical features of wood. In Proceedings of the 1st European Symposium on Nondestructive Evaluation of Wood. Sopron, Hungary. p. 536.

Martínez, J.J. 1992. Características mecánicas de la madera de *Pinus pinaster* Ait. obtenidas a partir de ensayos con piezas de tamaño estructural (Mechanical properties of *Pinus pinaster* Ait. structural timber). Ph.D. Thesis, UPM, Madrid, Spain.

Martínez, R.D.; Bobadilla, I. 2013. Extractor de muestras de madera mediante taladro (Wood sample extractor using a conventional drill). Spain, ES2525504. (B27C 3/00) (2006.1). Appl. 201330890. https://patentscope.wipo.int/search/es/detail.jsf?docId=ES132634337&_cid=P22-K403XF-18800-1.

Martínez, R.D. 2016. Métodos no destructivos de estimación de la densidad de madera. (Timber density estimation by non-destructive methods). Ph.D. Thesis. USC, Lugo, Spain. <http://hdl.handle.net/10347/15159>.

Martínez, R.D.; Calvo, J.; Arriaga, F.; Bobadilla, I. 2018. In situ density estimation of timber pieces by drilling residue analysis. *Eur J Wood Prod* 76: 509-515. <https://doi.org/10.1007/s00107-017-1214-7>.

Martínez-Sala, R.; Rodríguez-Abad, I.; Díez, M.R.; Capuz, R. 2013. Assessment of the dielectric anisotropy in timber using the nondestructive GPR technique. *Constr Build Mater* 38: 903-911. <https://doi.org/10.1016/j.conbuildmat.2012.09.052>.

Merlo, E.; Álvarez-González, J.G.; Santaclara, O.; Riesco, G. 2014. Modelling modulus of elasticity of *Pinus pinaster* Ait. in northwestern Spain with standing tree acoustic measurements, tree, stand and site variables. *Forest Syst* 23(1): 153-166. <http://dx.doi.org/10.5424/fs/2014231-04706>.

Mier, R. 2001. Clasificación de madera aserrada estructural mediante Inteligencia Artificial: Redes Neuronales (Structural sawn timber classification by artificial intelligent: Neural Networks). Final Project Degree. UPM, Madrid, Spain.

Montero, M.J. 2013. Clasificación de madera estructural de gran escuadría de *Pinus sylvestris* L. mediante métodos no destructivos (Grading of large cross section structural timber of *Pinus sylvestris* L. by non destructive techniques). Ph.D. Thesis, UPM, Madrid, Spain. <http://oa.upm.es/15201/>.

Montero, M.J.; de la Mata, J.; Esteban, M.; Hermoso, E. 2015. Influence of moisture content on the wave velocity to estimate the mechanical properties of large cross-section pieces for structural use of Scots pine from Spain. *Maderas-Cienc Tecnol* 17(2): 407-420. <http://dx.doi.org/10.4067/S0718-221X2015005000038>.

Montón, J. 2012. Clasificación estructural de la Madera de *Pinus radiata* D. Don procedente de Cataluña mediante métodos no destructivos y su aplicabilidad en la diagnosis estructural (Structural timber grading of *Pinus radiata* D. Don from Catalonia using NDT and applicability in structural assessment). Ph.D. Thesis. UPC, Barcelona, Spain. <https://www.tdx.cat/handle/10803/96423#page=1>.

Montón, J.; Arriaga, F.; Íñiguez-González, G.; Segué, E. 2015. Warp requirements and yield efficiency in the visual grading of sawn radiata pine timber. *BioResources* 10(1): 1115-1126. <https://bioresources.cnr.ncsu.edu/resources/warp-requirements-and-yield-efficiency-in-the-visual-grading-of-sawn-radiata-pine-timber/>.

Montoya-Morgu, F. 2010. Creació d'una metodologia d'aplicació i assaig del Resistògraf en la diagnosi d'elements estructurals de fusta (Resistograph application and evaluation methodology development for assessment of timber structures). Final Project Degree. UPC, Barcelona, Spain.

Morales-Conde, M.J.; Rodríguez-Liñán, C.; Rubio, P. 2013. Application of non-destructive techniques in the inspection of the wooden roof of historic buildings: A case study. In Proceedings of the 2nd International

Conference on Structural Health Assessment of Timber Structures (SHATIS). Trento, Italy. pp. 233-242.

Morales-Conde, M.J.; Rodríguez-Liñán, C.; Machado, J.S. 2014. Predicting the density of structural timber members in service. The combined use of wood cores and drill resistance data. *Mater Construcc* 64(315): e029. <http://dx.doi.org/10.3989/mc.2014.03113>.

Morales-Conde, M.J.; Machado, J.S. 2017. Evaluation of cross-sectional variation of timber bending modulus of elasticity by stress waves. *Constr Build Mater* 134: 617-625. <https://doi.org/10.1016/j.conbuildmat.2016.12.188>.

Oliver, J.V.; Abián, M.A. 2013. Advanced wireless sensors for termite detection in wood constructions. *Wood Sci Technol* 47: 269-280. <https://doi.org/10.1007/s00226-012-0485-8>.

Osuna-Sequera, C. 2017. Particularidades de la aplicación de las técnicas no destructivas en la estimación de propiedades mecánicas en piezas de madera de gran longitud procedentes de estructuras existentes (Considerations on non-destructive testing applied to estimate mechanical properties in large length timber pieces from existing structures). Final Project Degree. UPM, Madrid, Spain. <http://oa.upm.es/51760/>.

Osuna-Sequera, C.; Íñiguez-González, G.; Esteban, M.; Llana, D.F.; Arriaga, F. 2017. Particularidades de la aplicación de las técnicas no destructivas en piezas de madera de gran longitud procedentes de estructuras existentes (Considerations on the application of nondestructive testing on large length timber pieces from existing structures). In Proceedings of LIGNOMAD 17 the 1º Congreso sobre Construcción con Madera y otros Materiales Lignocelulósicos. Barcelona, Spain. pp. 53-57.

Osuna-Sequera, C.; Llana, D.F.; Íñiguez-González, G.; Arriaga, F. 2019a. The influence of cross-section variation on bending stiffness assessment in existing timber structures. *Eng Struct*. 204(2020): 110082. <https://doi.org/10.1016/j.engstruct.2019.110082>.

Osuna-Sequera, C.; Llana, D.F.; Esteban, M.; Arriaga, F. 2019b. Improving density estimation in large cross-section timber from existing structures by increasing the number of non-destructive measurements. *Constr Build Mater* 211: 199-206. <https://doi.org/10.1016/j.conbuildmat.2019.03.144>.

Palaia, L.; Galvañ, V.; Cervera, F.; Monzo, V. 1993. Using ultrasonic waves for the detection of timber decay in old buildings. In Proceedings of the 9th International Symposium on Nondestructive Testing of Wood. Madison, WI, USA. pp. 71-77.

Palaia, L.; Galvañ, V.; Cervera, F.; Molina, R. 2000. NDT determination of the strength loss of deteriorated wood, by using ultrasonic techniques and a specific wood tester. In Proceedings of the 12th International Symposium on Nondestructive Testing of Wood. Sopron, Hungary. pp. 327-336.

Palaia, L.; Monfort, J.; Sánchez, R.; Gil, L.; Álvarez, Á.; López, V.; Tormo, S.; Pérez, C.; Navarro, P. 2008. Assessment of timber structures in service by using combined methods of non-destructive testing together with traditional ones. In Proceedings of the 9th International Conference on NDT of Art. Jerusalem, Israel. 10 p.

Pedras, F.; Riesco G.; Remacha, A. 1997. Determinación de las características elásticas de la madera de castaño (*Castanea sativa* Mill.) mediante ensayos no destructivos (Determination of elastic properties of sweet chestnut (*Castanea sativa* Mill.) by NDT). In Proceedings of the 2º Congreso Forestal Español. Pamplona, Spain. pp. 295-300.

Pérez-García, A. 2012. Estimación de parámetros de calidad sobre tableros derivados de la madera a partir de ensayos no destructivos (Wood-board quality parameter estimation by non-destructive testing). Final Project Degree. UPM, Madrid, Spain. <http://oa.upm.es/11295/>.

Riesco, G. 2001. Estudio de las propiedades físico-mecánicas de la madera de roble (*Quercus robur* L.) de Galicia en relación con las variables del medio (Study of physico-mechanical properties of European oak (*Quercus robur* L.) timber from Galicia in relation with environmental variables). Ph.D. Thesis, UPM, Madrid, Spain.

Rodríguez-Abad, I.; Martínez-Sala, R.; Capuz, R.; Díez, M.R.; García-García, F. 2011. Estudio de la variación del contenido de humedad en el *Pinus pinaster* Ait. por medio de la técnica no destructiva del geor-

radar (Assessment of the variation of the moisture content in *Pinus pinaster* Ait. using the non destructive GPR technique). *Mater Construcc* 61(301): 143-156. <https://doi.org/10.3989/mc.2010.49608>.

Rodríguez-Liñán, C.; Rubio, P. 1995. Evaluación del estado de la madera, en obras de rehabilitación, mediante técnicas de ultrasonidos y obtención de parámetros resistentes (Evaluation of wood conservation works by ultrasound techniques and obtention of resistance parameters). *Inf Constr* 47(440): 5-22. <https://doi.org/10.3989/ic.1995.v47.i440.1044>.

Rodríguez-Liñán, C.; Rubio, P. 2000. Evaluación del estado de la madera, en obras de rehabilitación, mediante técnicas de ultrasonidos (Timber assessment by ultrasound techniques in refurbishment works). Universidad de Sevilla, Secretariado de Publicaciones, Instituto Universitario de Ciencias de la Construcción: Sevilla, Spain. <https://expobus.us.es/omeka/items/show/883>.

Rojas, J.A.M.; Alpuente, J.; Postigo, D.; Rojas, I.M.; Vignote, S. 2011. Wood species identification using stress-wave analysis in the audible range. *Appl Acoust* 72: 934-942. <https://doi.org/10.1016/j.apacoust.2011.05.016>.

Ruano, A.; Zitek, A.; Hinterstoisser, B.; Hermoso, E. 2019. NIR hyperspectral imaging (NIR-HI) and μ XRD for determination of the transition between juvenile and mature wood of *Pinus sylvestris* L. *Holzfor-schung* 73(7): 621-627. <https://doi.org/10.1515/hf-2018-0186>.

Rubio, P. 1997. Evaluación del estado de la madera mediante técnicas de ultrasonidos (Assessment of timber by ultrasound techniques). Ph.D. Thesis. US, Sevilla, Spain. <http://hdl.handle.net/11441/23937>.

Salamanca, M. 2017. Estimación mediante penetrometros de la densidad en madera aserrada de las especies de coníferas y frondosas más habituales en construcción en España (Study on the estimation, by penetrometers, of the density of sawn wood of the most common coniferous and leafy species used in construction in Spain). Final Project Degree. UPM, Madrid, Spain.

Sánchez-Beitia, S.; Crespo-de-Antonio, M.; Acuña, L. 2015. Applicability of the Hole-Drilling procedure for stresses quantification in timber bending elements in service. *Constr Build Mater* 93: 798-805. <https://doi.org/10.1016/j.conbuildmat.2015.05.091>.

Santaclara, O.; Fernández, A.; Merlo, E.; Guaita, M. 2009. Técnicas no destructivas y ensayo mecánico en madera aserrada de gran escuadría de *Pseudotsuga menziesii* (Nondestructive testing and mechanical testing of large cross-section *Pseudotsuga menziesii* sawn timber). In Proceedings of the V Congreso Nacional y II Congreso Ibérico AgroIngeniería. Lugo, Spain. 9 p.

Santaclara, O.; Merlo, E. 2011. Acoustic segregation of *Pinus pinaster* logs for structural lumber production according to strength classes. In Proceedings of the 17th International Nondestructive Testing and Evaluation of Wood Symposium. Sopron, Hungary. p. 755.

Sevilla, S.; Bobadilla, I.; Martínez, R.D.; Esteban, M.; Llana, D.F. 2013. Non-destructive methods to estimate the physical aging of Superpan. In Proceedings of the 18th International Nondestructive Testing and Evaluation of Wood Symposium. Madison, WI, USA. p. 637.

Soto-Martínez, I. 2010. Estudio de la relación entre perfiles de densidad y gráficas resistográficas en madera estructural y aplicaciones industriales (Comparison between density and resistograph results in structural timber and industrial applications). Final Project Degree. UPV, Gandía, Spain. <https://riunet.upv.es/handle/10251/9983>.

Touza, M.C. 2009. Case study: Assessment of the mechanical properties of an old pitch pine timber structure. In Proceedings of the International Conference on Wooden Cultural Heritage. Hamburg, Germany. 8 p.

Touza, M.C.; Soilán, A.; Lorenzo, D. 2013. Evaluation of the load-carrying capacity in bending of large cross section "Pitch pine" beams in standing structures. *Adv Mater Res-Switz* 778: 410-417. <https://doi.org/10.4028/www.scientific.net/AMR.778.410>.

Troya, M.T.; Navarrete, A. 1994. Study of the degradation of retified wood through ultrasonic and gravimetric techniques. In Proceedings of the 25th Annual meeting. Bali, Indonesia. 6 p.

UNE. 1972. Clasificación de la madera aserrada de construcción. UNE 56525. 1972. (Visual grading of construction sawn timber). IRANOR/CTN 56 Madera y Corcho: Madrid, Spain.

UNE. 2011. Clasificación visual de la madera aserrada para uso estructural. Madera de coníferas. UNE 56544. 2011. (Visual grading for structural sawn timber. Coniferous timber). AEN/CTN 56 Madera y Corcho: Madrid, Spain.

UNE. 2013. Clasificación visual de la madera aserrada para uso estructural. Madera de frondosas. UNE 56546. 2013. (Visual grading for structural sawn timber. Hardwood timber). AEN/CTN 56 Madera y Corcho: Madrid, Spain.

UNE. 2014. Estructuras de madera existentes. Uso del penetrómetro para el diagnóstico de los elementos de madera de edificios existentes. UNE 41809. 2014. (Existing wood structures. Use of penetrometer in wood elements diagnosis in existing buildings). AEN/CTN 41 Construcción: Madrid, Spain.

UNE. 2018. Clasificación visual de los postes de madera para líneas aéreas. UNE 56547. 2018. (Visual classification for wood overhead poles). CTN 56 Madera y Corcho: Madrid, Spain.

Vázquez, C.; Gonçalves, R.; Bertoldo, C.; Baño, V.; Vega, A.; Crespo, J.; Guaita, M. 2015. Determination of the mechanical properties of *Castanea sativa* Mill. using ultrasonic wave propagation and comparison with static compression and bending methods. *Wood Sci Technol* 49: 607-622. <https://doi.org/10.1007/s00226-015-0719-7>.

Vega, A.; Dieste, A.; Guaita, M.; Majada, J.; Baño, V. 2012. Modelling of the mechanical properties of *Castanea sativa* Mill. structural timber by a combination of nondestructive variables and visual grading parameters. *Eur J Wood Prod* 70(6): 839-844. <https://doi.org/10.1007/s00107-012-0626-7>.

Vega, A. 2013. Caracterización mecánica de la madera estructural de *Castanea sativa* Mill. clasificación visual y evaluación mediante métodos no destructivos (Mechanical characterization of *Castanea sativa* Mill. structural sawn timber: visual grading and nondestructive testing evaluation). Ph.D. Thesis. USC, Lugo, Spain. <https://minerva.usc.es/xmlui/handle/10347/9345>.

Vega, A.; Arriaga, F.; Guaita, M.; Baño, V. 2013. Proposal for visual grading criteria of structural timber of sweet chestnut from Spain. *Eur J Wood Prod* 71: 529-532. <https://doi.org/10.1007/s00107-013-0705-4>.

Vega, A.; González, L.; Fernández, I.; González, P. 2019a. Grading and mechanical characterization of small-diameter round chestnut (*Castanea sativa* Mill.) timber from thinning operations. *Wood Mater Sci Eng* 14(2): 81-87. <https://doi.org/10.1080/17480272.2017.1387174>.

Vega, A.; González, L.; Rodríguez, S.; Hevia, A. 2019b. Prediction of the sawing yield of *Pinus pinaster* and *Pinus radiata* structural timber from thinning operations through Nondestructive Techniques. In Proceedings of the 21st International Nondestructive Testing and Evaluation of Wood Symposium. Freiburg im Breisgau, BW, Germany. pp. 577-583.

Vilches, M.; Correal, E. 2009. Aplicación del resistógrafo para la determinación de las propiedades de la madera (Using a resistograph to determine wood properties). In Proceedings of the 5^o Congreso Forestal Español. Avila, Spain. 8 p.

Vilches, M.; Labèrnia, C.; Rodríguez, V. 2015. Assessment through NDT of the state of timber structures of the historic buildings of Catalonia. COST Action FP 1101 Assessment, reinforcement and monitoring of timber structures. pp 209-216.

Villacorta-Calvo, J.J.; Izquierdo-Fuente, A.; Val-Puente, L.; Suárez, L.; Martínez, R.D.; Morillas, L.; Basterra, L.A. 2019. AmemoMe: Diseño e implementación de un sistema de medida basado en acelerómetros MEMS para el análisis de los modos de vibración de una estructura de madera (AmemoMe: Accelerometers MEMS measurement system design and implementation to analyze vibration modes on a timber structure). In Proceedings of LIGNOMAD 19 the 2^o Congreso sobre Construcción con Madera y otros Materiales Lignocelulósicos. Santiago de Compostela, Spain. pp. 72-76.

Villanueva, J.L. 2009. Caracterización mecánica de rollizos de sabina (*Juniperus thurifera* L.) de Castilla y León. Prueba de clasificación visual y evaluación mediante resonancia (Mechanical characterization

of Spanish juniper (*Juniperus thurifera* L.) round timber from Castilla y León. Visual grading and resonance evaluation). Final Project Degree. UdL, Lérida, Spain. <https://repositori.udl.cat/handle/10459.1/45926>.

Villasante, A.; Íñiguez-González, G.; Puigdomenech, L. 2019. Comparison of various multivariate models to estimate structural properties by means of non-destructive techniques (NDTs) in *Pinus sylvestris* L. timber. *Holzforschung*. 73(4): 331-338. <https://doi.org/10.1515/hf-2018-0103>.